This item was submitted to [Loughborough's Research Repository](#) by the author.
Items in Figshare are protected by copyright, with all rights reserved, unless otherwise indicated.

A lead-free high-Curie-point ferroelectric ceramic, $\text{CaBi}_2\text{Nb}_2\text{O}_9$

PLEASE CITE THE PUBLISHED VERSION

<http://dx.doi.org/10.1002/adma.200401860>

PUBLISHER

© 2005 WILEY-VCH Verlag GmbH & Co. KGaA, Weinheim

VERSION

NA (Not Applicable or Unknown)

PUBLISHER STATEMENT

This work is made available according to the conditions of the Creative Commons Attribution-NonCommercial-NoDerivatives 4.0 International (CC BY-NC-ND 4.0) licence. Full details of this licence are available at:
<https://creativecommons.org/licenses/by-nc-nd/4.0/>

LICENCE

CC BY-NC-ND 4.0

REPOSITORY RECORD

Yan, Haixue, Hongtao Zhang, Rick Ubic, Michael J. Reece, Jing Liu, Zhijian Shen, and Zhen Zhang. 2015. "A Lead-free High-curie-point Ferroelectric Ceramic, $\text{CaBi}_2\text{Nb}_2\text{O}_9$ ". figshare. <https://hdl.handle.net/2134/17763>.

96.3, 93.0, 91.3, 90.5, 87.2, 40.2, 29.7, -0.09. Fast-ion bombardment MS: m/z 417 $[M]^+$, 402 $[M-Me]^+$, 386 $[M-2Me]^+$, 372 $[M-NMe_2]^+$, 345 $[M-SiMe_3]^+$, 300 $[M-NMe_2-SiMe_3]^+$. $T_d = 245^\circ\text{C}$.

Dimethyl-[4-(4-[(triisopropylsilyl)ethynyl]phenylethynyl)phenylethynyl]phenylethynyl]phenylamine (3): Yield: 89%. Anal. Calcd. for $C_{35}H_{39}NSi$: C, 83.78; H, 7.83; N, 2.79. Found: C, 83.24; H, 7.61; N, 2.34. ^1H NMR (400 MHz, CDCl_3): δ 7.48–7.38 (m, 10H), 6.68–6.63 (m, 2H), 3.00 (s, 6H), 1.13 (s, 21H). ^{13}C NMR (100 MHz, CDCl_3): δ 150.3, 132.8, 132.0, 131.5, 131.3, 131.2, 124.3, 123.4, 123.0, 121.8, 111.8, 109.7, 106.7, 93.0, 92.9, 91.2, 90.6, 87.3, 40.2, 18.7, 11.3, 0.0. FAB MS: m/z 501 $[M]^+$. $T_d = 315^\circ\text{C}$.

For the bottom-contact devices, layers of the oligo(arylacetylene)s with thicknesses of ca. 50 nm were deposited on the Au-patterned SiO_2/Si substrates at room temperature under high-vacuum condition (3×10^{-4} Pa). For the top-contact devices, the active organic layer (50 nm) was deposited on 100 nm SiO_2 substrates followed by the deposition of a gold electrode on the top using different masks for organic and metal layers. The devices fabricated on untreated substrates were tested in a microprobe station to measure the current–voltage characteristics of the devices under ambient conditions.

Received: December 7, 2004

Final version: February 12, 2005

- [1] G. Horowitz, *Adv. Mater.* **1998**, *10*, 365.
- [2] F. Garnier, *Chem. Phys.* **1998**, *227*, 253.
- [3] H. E. Katz, *J. Mater. Chem.* **1997**, *7*, 369.
- [4] F. Garnier, R. Hajlaoui, A. Yassar, P. Srivastava, *Science* **1994**, *265*, 1684.
- [5] C. D. Dimitrakopoulos, P. R. L. Malenfant, *Adv. Mater.* **2002**, *14*, 99.
- [6] B. Comiskey, J. D. Albert, H. Yoshizawa, J. Jacobson, *Nature* **1998**, *394*, 253.
- [7] M. L. Chabiny, A. Salleo, *Chem. Mater.* **2004**, *16*, 4509.
- [8] M. Halik, H. Klauk, U. Zschieschang, G. Schmid, C. Dehm, M. Schütz, S. Maisch, F. Effenberger, M. Brunnbauer, F. Stellacci, *Nature* **2004**, *431*, 963.
- [9] O. D. Jurchescu, J. Baas, T. T. M. Palstra, *Appl. Phys. Lett.* **2004**, *84*, 3061.
- [10] F. Garnier, R. Hajlaoui, A. El Kassmi, G. Horowitz, L. Laigre, W. Porzio, M. Armanini, F. Provasoli, *Chem. Mater.* **1998**, *10*, 3334.
- [11] a) H. Sirringhaus, N. Tessler, R. H. Friend, *Science* **1998**, *280*, 1741. b) H. Sirringhaus, P. J. Brown, R. H. Friend, M. M. Nielsen, K. Bechgaard, B. M. W. Langeveld-Voss, A. J. H. Spiering, R. A. J. Janssen, E. W. Meijer, P. Herwig, D. M. de Leeuw, *Nature* **1999**, *401*, 685. c) R. D. McCullough, *Adv. Mater.* **1998**, *10*, 93.
- [12] J. G. Laquindanum, H. E. Katz, A. J. Lovinger, *J. Am. Chem. Soc.* **1998**, *120*, 664.
- [13] R. E. Martin, F. Diederich, *Angew. Chem. Int. Ed.* **1999**, *38*, 1350.
- [14] a) A. Beeby, K. Findlay, P. J. Low, T. B. Marder, *J. Am. Chem. Soc.* **2002**, *124*, 8280. b) J. Kim, I. A. Levitsky, D. T. McQuade, T. M. Swager, *J. Am. Chem. Soc.* **2002**, *124*, 7710. c) J. Cornil, Y. Karzazi, J. L. Brédas, *J. Am. Chem. Soc.* **2002**, *124*, 3516. d) M. I. Sluch, A. Godt, U. H. F. Bunz, M. A. Berg, *J. Am. Chem. Soc.* **2001**, *123*, 6447. e) M. Levitus, K. Schmieder, H. Ricks, K. D. Shimizu, U. H. F. Bunz, M. A. Garcia-Garibay, *J. Am. Chem. Soc.* **2001**, *123*, 4259.
- [15] a) A. M. McDonagh, M. G. Humphrey, M. Samoc, B. Luther-Davies, S. Houbrechts, T. Wada, H. Sasabe, A. Persoons, *J. Am. Chem. Soc.* **1999**, *121*, 1405. b) K. D. John, M. D. Hopkins, *Chem. Commun.* **1999**, 589. c) Y. G. Ma, W. H. Chan, X. M. Zhou, C. M. Che, *New J. Chem.* **1999**, *23*, 263. d) S. C. Chan, M. C. W. Chan, Y. Wang, C. M. Che, K. K. Cheung, N. Y. Zhu, *Chem. Eur. J.* **2001**, *7*, 4180. e) W. Lu, B. X. Mi, M. C. W. Chan, Z. Hui, N. Y. Zhu, S. T. Lee, C. M. Che, *Chem. Commun.* **2002**, 206. f) H. Y. Chao, W. Lu, Y. Li, M. C. W. Chan, C. M. Che, K. K. Cheung, N. Y. Zhu, *J. Am. Chem. Soc.* **2002**, *124*, 14696.
- [16] S. Anderson, *Chem. Eur. J.* **2001**, *7*, 4706.

- [17] a) U. H. F. Bunz, *Chem. Rev.* **2000**, *100*, 1605. b) A. Kraft, A. C. Grimsdale, A. B. Holmes, *Angew. Chem. Int. Ed.* **1998**, *37*, 402. c) C. Weder, C. Sarwa, A. Montali, C. Bastiaansen, P. Smith, *Science* **1998**, *279*, 835. d) A. Montali, C. Bastiaansen, P. Smith, C. Weder, *Nature* **1998**, *392*, 261.
- [18] J. M. Tour, *Acc. Chem. Res.* **2000**, *33*, 791.
- [19] D. T. McQuade, A. E. Pullen, T. M. Swager, *Chem. Rev.* **2000**, *100*, 2537.
- [20] K. T. Wong, F. C. Fang, Y. M. Cheng, P. T. Chou, G. H. Lee, Y. Wang, *J. Org. Chem.* **2004**, *69*, 8038.
- [21] Z. J. Donhauser, B. A. Mantooth, K. F. Kelly, L. A. Bumm, J. D. Monnell, J. J. Stapleton, D. W. Price, Jr., A. M. Rawlett, D. L. Al-lara, J. M. Tour, P. S. Weiss, *Science* **2001**, *292*, 2303.
- [22] a) K. Sonogashira, Y. Tohda, N. Hagihara, *Tetrahedron Lett.* **1975**, *16*, 4467. b) O. Lavastre, L. Ollivier, P. H. Dixneuf, S. Sibandhit, *Tetrahedron* **1996**, *52*, 5495.
- [23] M. J. Powell, *Appl. Phys. Lett.* **1983**, *43*, 597.
- [24] M. Matters, D. M. de Leeuw, P. T. Herwig, A. R. Brown, *Synth. Met.* **1999**, *102*, 998.

A Lead-Free High-Curie-Point Ferroelectric Ceramic, $\text{CaBi}_2\text{Nb}_2\text{O}_9$ **

By Haixue Yan, Hongtao Zhang, Rick Ubic, Michael J. Reece,* Jing Liu, Zhijian Shen, and Zhen Zhang

High-temperature sensing technology is of major importance for chemical and material processing, as well as the automotive, aerospace, and power-generating industries. Electro-mechanical transducing materials are required to sense strains, vibrations, and noise under severe thermal conditions. Among the different types of acoustic and strain sensors, piezoelectrics offer the best candidates when one considers sensitivity, cost, and design.^[1] When an operating temperature of 400°C or greater is required, the choice of materials for high-temperature piezoelectric transducers is limited. Although some single crystals such as LiNbO_3 ,^[1] $\text{La}_3\text{Ga}_5\text{SiO}_{14}$,^[2,3] $\text{Sr}_2\text{Nb}_2\text{O}_7$,^[4] and $\text{A}_2\text{Ti}_2\text{O}_7$ (where A is La or Nd)^[5] are good commercial or potential candidates for high-temperature piezoelectric applications, the cost of single crystals is very much higher than that of polycrystalline piezoceramics.^[1,2] Another important ad-

[*] Dr. M. J. Reece, Dr. H. Yan, H. Zhang, Dr. R. Ubic
Department of Materials, Queen Mary University of London
Mile End Road, London, E1 4NS (UK)
E-mail: m.j.reece@qmul.ac.uk

J. Liu, Dr. Z. Shen
Department of Inorganic Chemistry, Arrhenius Laboratory
Stockholm University
S-10691, Stockholm (Sweden)
Z. Zhang
Shanghai Institute of Ceramics, Chinese Academy of Sciences
1295 Dingxi Road, Shanghai, 200050 (P. R. China)

[**] This research was funded by QinetiQ Ltd under contract number CU004-16541 and the Swedish Research Council through grant 621-2002-4299.

vantage^[2] of polycrystalline piezoceramics over single crystals is the ease with which composition and properties may be tailored. Modified bismuth titanate compositions are interesting for sensor applications up to 500 °C.^[2] When an operating temperature of up to 750 °C is required, there is no suitable commercial polycrystalline ceramic available.^[1,2] In this communication, we report on a textured lead-free high-Curie-point (T_c) ferroelectric polycrystalline ceramic, $\text{CaBi}_2\text{Nb}_2\text{O}_9$ (CBNO), which has the highest-known T_c (943 °C) of the Aurivillius-phase-structured materials, and the highest thermal-depoling temperature (800 °C) for a polycrystalline ferroelectric ceramic. The T_c corresponds to the paraelectric–ferroelectric transition and is associated with an anomaly in the dielectric constant. It therefore sets the upper temperature limit on the application of ferroelectric ceramics for piezoelectric applications. The CBNO ceramic is a good lead-free candidate for high-temperature piezoelectric applications up to 800 °C.

Both bismuth titanate ($\text{Bi}_4\text{Ti}_3\text{O}_{12}$) and CBNO are bismuth layer-structured ferroelectrics (BLSFs) in the Aurivillius phase family of materials. Aurivillius materials have attracted considerable attention for their potential use in non-volatile ferroelectric random-access memory (FRAM)^[6,7] and high-temperature piezoelectric applications^[8,9] because they are fatigue-free and have high values of T_c , respectively. The general formula of Aurivillius phase materials is $(\text{Bi}_2\text{O}_2)^{2+}(\text{A}_{m-1}\text{B}_m\text{O}_{3m+1})^{2-}$, where A is a mono-, di-, or trivalent element (or combination) with cuboctahedral coordination, B is a transition element suited to octahedral coordination, and m is the number of octahedral layers in the perovskite slab. The m value can vary from 1 to 6.^[10] The spontaneous polarization P_s for $\text{CaBi}_2\text{Nb}_2\text{O}_9$ is along the a -axis direction. As a consequence of the anisotropy of microstructures and the properties of Aurivillius phase materials, texturing technologies, such as hot-forging^[11] and templated grain growth,^[9] can improve their electrical properties. Spark plasma sintering (SPS) is a new sintering process. It enhances the densification and superplastic deformation of ceramics through pulsed-electrical-current heating, producing high-density, textured materials.^[12,13] To our knowledge, there are so far no reports on the microstructures or properties of textured CBNO ceramics. In the present work, piezoelectric ceramics $\text{CaBi}_2\text{Nb}_2\text{O}_9$ were fabricated by ordinary firing (OF) and SPS.

Figure 1 shows X-ray diffraction (XRD) patterns of SPS ceramic surfaces cut perpendicular and parallel to the hot-pressing direction compared with a pattern of non-textured OF CBNO ceramic. The diffraction peaks are matched and indexed based on CBNO^[14] crystal-structure parameters. The materials are all single-phase within the sensitivity of the technique. The XRD pattern parallel to the hot-pressing direction exhibited strong (00 l) diffraction peaks, while the pattern perpendicular to the hot-pressing direction showed weak (00 l) peaks and a strong (020)/(200) peak. This indicates that the SPS samples were highly textured. The strongest diffraction peak for OF CBNO was (115), which is consistent with the

Figure 1. XRD patterns of CBNO surface obtained by cutting a) perpendicular and b) parallel to the hot-pressing direction in SPS samples, and c) OF sample.

(112 m +1) highest diffraction peak in Aurivillius phases.^[15] Figure 2 shows the secondary electron scanning electron microscopy (SEM) images of the polished then thermally etched surfaces perpendicular and parallel to the hot-pressing direction of the SPS and OF CBNO ceramics. The grains are oriented for the SPS sample, which is consistent with the XRD results in Figure 1.

Pure CBNO has $A2_1am$ orthorhombic symmetry^[16] with the polarization along the a -axis. Atomic displacements along the a -axis from the corresponding positions in the parent tetragonal ($I4/mmm$) structure cause ferroelectric spontaneous polarization P_s . Polarization caused by displacements along the b - and c -axes are cancelled due to the presence of glide and mirror planes, respectively, and thus do not contribute to the total P_s . Based on the atomic displacements, the total P_s of the displacive-type ferroelectric CBNO was calculated using Shimakawa's model,^[17]

$$P_s = \sum_i \frac{m_i \Delta x_i Q_i e}{V} \quad (1)$$

where m_i is the site multiplicity, Δx_i is the atomic displacement along the a -axis from the corresponding position in the tetragonal structure, $Q_i e$ is the ionic charge of the i th constituent ion, and V is the volume of the unit cell. In terms of the crystal structure parameters of CBNO reported by Blake et al.,^[18] the ion displacements along the a -axis and the contributions of each constituent ion to the total ferroelectric polarization are calculated in Figure 3. Based on Rietveld analysis of XRD and neutron-diffraction data, Blake et al.^[18] suggested that CBNO showed some chemical disorder on both the perovskite A-site and Bi_2O_2 layer. There is about 5.3 at.% calcium on the bismuth site in the Bi_2O_2 layer. The calcium in

Figure 2. Secondary electron SEM images of polished then thermally etched surfaces for a) perpendicular, b) parallel to the hot-pressing direction in SPS samples, c) OF sample.

the Bi_2O_3 layer and bismuth in A-site are labeled as Ca(2) and Bi(1), respectively, in Figure 3.

Figure 4 shows the polarization–electric field (P – E) hysteresis loops for CBNO samples. The remanent polarization $P_r [\perp]$ is highest perpendicular to the hot-pressing direction in the textured SPS sample. The reason for this is that the ferroelectric polarization switching occurs in the a – b plane in CBNO. Due to the lower limit on the sample thickness (0.10–0.15 mm) imposed by porosity and the maximum available voltage (4 kV) and the conductivity at high voltages, it was not possible to obtain saturated P – E hysteresis loops because of the evidently high coercive field (E_c) of CBNO. Similar problems have been previously noted for high- T_c $\text{Bi}_3\text{NbTiO}_9$ ceramics.^[8] Consequently, the values of $P_r [\perp]$ for CBNO are much less than the theoretical spontaneous polarization calculated in Figure 3.

In spite of their relatively large P_s , the piezoelectric activity of ordinary fired BLSFs ceramics is limited because of the two-dimensional orientation restriction of the rotation of their spontaneous polarization P_s and their high coercive field E_c . Textured processing is an effective method to improve piezoelectric activity of BLSFs because of the anisotropy of their

Figure 3. Ion displacement and contribution to the total spontaneous polarization P_s of each ion of $\text{CaBi}_2\text{Nb}_2\text{O}_9$.

Figure 4. P – E hysteresis loops of CBNO ceramics.

microstructures and properties. The average piezoelectric constant d_{33} of three samples each of SPS $[\perp]$, SPS $[\parallel]$, and OF CBNO samples were $19.5 \pm 0.3 \text{ pC/N}^{-1}$, $0.2 \pm 0.1 \text{ pC/N}^{-1}$, and $7.5 \pm 0.2 \text{ pC/N}^{-1}$, respectively.

Both $\text{Bi}_3\text{NbTiO}_9$ (BNT) and $\text{CaBi}_2\text{Nb}_2\text{O}_9$ (CBNO) are BLSFs with $m=2$ in which the A-site cations are Bi^{3+} and Ca^{2+} , respectively. The Curie point (914°C) of BNT^[19] is

higher than that reported by Ismailzade^[20] for CBNO (below 650 °C). This is inconsistent with Subbarao's suggestion^[21] that the Curie point of Aurivillius-phase materials increases with the decrease in the A-site cation size because the effective radius of Ca^{2+} is smaller than that of Bi^{3+} .^[22] Figure 5 shows the temperature dependence of dielectric constant (ϵ_r) and loss (D) of CBNO at 1 MHz. We also studied the temperature dependence of the dielectric constant at different frequencies

Figure 5. Temperature dependence of dielectric constant (ϵ_r) and loss (D) in CBNO ceramics.

and found no dispersion in the temperature of the dielectric anomaly. The Curie point of SPS CBNO samples perpendicular and parallel to the hot-pressing direction was 943 ± 2 °C, which is very close to that of OF CBNO ceramics (940 ± 2 °C). These values of the Curie point are much higher than the 650 °C reported by Ismailzade^[20] for CBNO. The fact that the Curie point (940 °C) of CBNO was found to be higher than that of BNT0 (914 °C)^[19] is consistent with Subbarao's work.^[21] The effective radius of Ca^{2+} is smaller than that of Bi^{3+} for any coordination.^[22] Ismailzade's result^[20] for T_c may be in error because it was obtained with the assumption that it coincided with a phase transformation observed by XRD. The piezoelectric constant of BNT0 is also lower than that of CBNO.

The dielectric constant and loss in the SPS samples is greater perpendicular to than parallel to the hot-pressing direction. The dielectric constant of OF CBNO is smaller than that of both SPS $[\perp]$ and SPS $[\parallel]$ CBNO at room temperature. Similar results were found by Seth and Schulze^[23] in textured $\text{Bi}_4\text{Ti}_3\text{O}_{12}$ ceramics. At higher temperatures (~ 400 °C), the dielectric constant of OF samples is lower than that of SPS $[\perp]$ but higher than that of SPS $[\parallel]$ samples. This behavior is the typical dependence of dielectric constant on temperature for BLSFs.^[11,24] The loss peaks just below the Curie points can be attributed to the movement of domain walls in BLSFs.

The thermal-depoling behavior of the OF and SPS $[\perp]$ CBNO samples is shown in Figure 6, in which piezoelectric

Figure 6. Effect of annealing temperature (for 2 h) on the piezoelectric constant d_{33} of CBNO ceramics.

constants d_{33} are plotted against the annealing temperature. The d_{33} value of OF CBNO decreased slightly with temperature up to 400 °C and was then stable up to 800 °C. The d_{33} of the SPS $[\perp]$ sample was stable up to 800 °C, and dropped rapidly above 900 °C.

In summary, the ferroelectric, dielectric, and piezoelectric properties of single-phase OF and SPS $\text{CaBi}_2\text{Nb}_2\text{O}_9$ ceramics were characterized. The Curie point of textured $\text{CaBi}_2\text{Nb}_2\text{O}_9$ (943 °C) was found to be much higher than its previously reported value (below 650 °C). The calculated total P_s of $\text{CaBi}_2\text{Nb}_2\text{O}_9$ is $24.4 \mu\text{C cm}^{-2}$. The d_{33} of textured materials was nearly three times that of conventionally sintered materials. Thermal-depoling studies demonstrated that d_{33} was stable up to 800 °C in textured $\text{CaBi}_2\text{Nb}_2\text{O}_9$. Therefore, a combination of high T_c , stable d_{33} , and high thermal-depoling temperature indicates that textured CBNO is a very promising material for high-temperature (up to 800 °C) piezoelectric applications.

Experimental

The starting materials were Bi_2O_3 of 99.975 % purity, CaCO_3 of 99 % purity, and Nb_2O_5 of 99.9 % purity. The CBNO powders were calcined at 950 °C for 4 h. The textured CBNO ceramics were prepared by SPS using a Dr. Sinter 2050 facility (Sumitomo Coal Mining Co. Ltd., Japan). At first, the CBNO powder was consolidated in a graphite die at 925 °C for 3 min under a pressure of 100 MPa to produce a dense ceramic. The fully densified ceramic tablet with a diameter of 12 mm and thickness of 7.3 mm was then deformed in another graphite die with a larger inner diameter of 20 mm at 1150 °C for 5 min under a constant load that corresponded to an initial compressive stress of 40 MPa to reach a total strain of 67 %. The heating rate for SPS was $100^\circ\text{C min}^{-1}$. In order to remove the carbon from the textured samples, the ceramics were subsequently annealed at 1000 °C for 4 h in air. The textured ceramics were cut perpendicular and parallel to the hot-pressing direction. The OF CBNO ceramics were sintered at 1065 °C for 1 h in air.

XRD patterns for the ceramics were obtained with an X-ray diffractometer (Siemens D5000) using $\text{Cu K}\alpha$ radiation. The microstructures of the ceramic samples were observed by SEM (JEOL JSM 6300). The SEM samples were thermally etched at about 70 °C below their sintering temperatures for 15 min to reveal their grain structure.

Electrodes for room-temperature and high-temperature electrical-property measurements were fabricated with fired-on silver paste (Johnson Matthey, E1100) and palladium paste (Gwent Electronic Materials Ltd., C2011004D5), respectively. Samples for piezoelectric measurements were poled in silicone oil at 200 °C under various direct-current (DC) electric fields (15–20 kV mm⁻¹). The piezoelectric constant d_{33} was measured using a quasi-static d_{33} meter (CAS, ZJ-3B). The ferroelectric polarization–electric field (P – E) hysteresis loops were measured by a ferroelectric hysteresis measurement tester (NPL, UK). The temperature dependence of dielectric constant and loss were measured at 1 MHz using an Agilent 4284A LCR meter connected to a furnace. Thermal-depoling experiments were conducted by holding the poled samples with Pt electrodes for 2 h at various high temperatures, cooling to room temperature, measuring d_{33} , and repeating the procedure up to 950 °C.

Received: November 12, 2004
Final version: January 27, 2005

Self-Organization of Semiconducting Polysiloxane-Phthalocyanine on a Graphite Surface**

By Paolo Samorì,* Hans Engelkamp,
Pieter A. J. de Witte, Alan E. Rowan,
Roeland J. M. Nolte,* and Jürgen P. Rabe*

The fabrication of molecular or supramolecular wires^[1] requires the design of rod-like objects with an intrinsic electrical conductivity, a notable stiffness, and a length on the order of tens of nanometers. An ordered assembly of these anisometric nanostructures should be possible in thin films. Post treatments such as thermal annealing have been successfully used to increase the degree of order in submicrometer sized molecular architectures assembled at surfaces^[2–4] and, on the tens of nanometers scale, in long monodisperse alkane layers.^[5] Scanning force microscopy (SFM)^[6] and scanning tunneling microscopy (STM)^[7] offer direct access to the structural properties of (macro)molecules over a wide range of length scales spanning from the subnanometer up to the micrometer scale.^[8]

Here, we report on the effect of thermally induced self-organization at elevated temperatures in dry ultrathin films consisting of rod-like semiconducting polymers, assembled on graphite and characterized on the single molecule scale. Moreover, we compare these results with those obtained by studying the solvent-induced columnar ordering of the same macromolecules at the solid–liquid interface. While the former approach is technologically more interesting, the latter provides useful insight into the potential of the wet-processing to obtain ordered nanostructures at surfaces.

The rod-like object chosen is a functionalized phthalocyaninato-polysiloxane (PSPc) (Fig. 1).^[9] Its monomeric phthalocyanine

- [1] R. C. Turner, P. A. Fuierer, R. E. Newnham, T. R. Shrout, *Appl. Acoust.* **1994**, *41*, 299.
- [2] D. Damjanovic, *Curr. Opin. Solid-State Mater. Sci.* **1998**, *3*, 469.
- [3] J. Hornsteiner, E. Born, E. Riha, *Phys. Status Solidi A* **1997**, *163*, R3.
- [4] S. Nanamatsu, M. Kimura, T. Kawamura, *J. Phys. Soc. Jpn.* **1975**, *38*, 817.
- [5] J. K. Yamaoto, A. S. Bhalla, *J. Appl. Phys.* **1991**, *70*, 4469.
- [6] C. Dearaujo, J. D. Cuchiaro, L. D. McMillan, M. C. Scott, J. F. Scott, *Nature* **1995**, *374*, 627.
- [7] B. H. Park, B. S. Kang, S. D. Bu, T. W. Noh, J. Lee, W. Jo, *Nature* **1999**, *401*, 682.
- [8] L. Pardo, A. Castro, P. Millan, C. Alemany, R. Jimenez, B. Jimenez, *Acta Mater.* **2000**, *48*, 2421.
- [9] S. H. Hong, S. Trolier-McKinstry, G. L. Messing, *J. Am. Ceram. Soc.* **2000**, *83*, 113.
- [10] Y. Wu, M. J. Forbess, S. Seraji, S. J. Limmer, T. P. Chou, C. Nguyen, G. Cao, *J. Appl. Phys.* **2001**, *90*, 5296.
- [11] K. Shoji, M. Aikawa, Y. Uehara, K. Sakata, *Jpn. J. Appl. Phys., Part 1* **1998**, *37*, 5273.
- [12] Z. Shen, H. Peng, M. Nygren, *Adv. Mater.* **2003**, *15*, 1006.
- [13] Z. Shen, E. Adolffson, M. Nygren, *Adv. Mater.* **2001**, *13*, 214.
- [14] Powder Diffraction File (PDF) No. 49-608.
- [15] X. F. Du, I. W. Chen, *J. Am. Ceram. Soc.* **1998**, *81*, 3253.
- [16] R. E. Newnham, R. W. Wolfe, J. F. Dorrian, *Mater. Res. Bull.* **1971**, *6*, 1029.
- [17] Y. Shimakawa, Y. Kubo, Y. Nakagawa, S. Goto, T. Kamiyama, H. Asano, F. Izumi, *Phys. Rev. B: Condens. Matter Mater. Phys.* **2000**, *61*, 6559.
- [18] S. M. Blake, M. J. Falconer, M. McCreedy, P. Lightfoot, *J. Mater. Chem.* **1997**, *7*, 1609.
- [19] Z. Zhang, H. Yan, P. Xiang, X. Dong, Y. Wang, *J. Am. Ceram. Soc.* **2004**, *87*, 602.
- [20] I. G. Ismailzade, *Bull. Acad. Sci. USSR, Phys. Ser. (Engl. Transl.)* **1960**, *24*, 1201.
- [21] E. C. Subbarao, *Phys. Chem. Solids* **1962**, *23*, 665.
- [22] R. D. Shannon, *Acta Crystallogr., Sect. A: Cryst. Phys. Diff., Theor. Gen. Crystallogr.* **1976**, *32*, 751.
- [23] V. K. Seth, W. A. Schulze, *IEEE Trans. Ultrason. Ferroelectr. Freq. Control* **1989**, *36*, 41.
- [24] T. Takenaka, K. Sakata, *Jpn. J. Appl. Phys.* **1980**, *19*, 31.

[*] Dr. P. Samorì
Istituto per la Sintesi Organica e la Fotoreattività, C.N.R.
via Gobetti 101, I-40129 Bologna (Italy)
E-mail: samori@isof.cnr.it

Dr. P. Samorì, Dr. P. A. J. de Witte
Institut de Science et d'Ingénierie Supramoléculaires
Université Louis Pasteur
8 Rue Gaspard Monge, F-67000 Strasbourg (France)
Prof. R. J. M. Nolte, Dr. H. Engelkamp, Prof. A. E. Rowan,
Dr. P. A. J. de Witte
NSRIM, Department of Organic Chemistry, University of Nijmegen
Toernooiveld, NL-6525 ED Nijmegen (The Netherlands)
E-mail: r.nolte@science.ru.nl

Prof. J. P. Rabe
Department of Physics, Humboldt University Berlin
Newtonstrasse 15, D-12489 Berlin (Germany)
E-mail: rabe@physik.hu-berlin.de

[**] This work was supported by the EU through the TMR project SISI-TOMAS (project reference FMRX970099), and the Marie Curie EST project SUPER, by the Deutsche Forschungsgemeinschaft (Sfb448 "Mesoskopisch strukturierte Verbundsysteme") and by the European Science Foundation both through the SMARTON and the EUROCORES-SONS-BIONICS programmes. Supporting Information is available online from Wiley InterScience or from the author.