This item was submitted to [Loughborough's Research Repository](#) by the author.
Items in Figshare are protected by copyright, with all rights reserved, unless otherwise indicated.

Polydimethylsiloxane and poly(ether) ether ketone functionally graded composites for biomedical applications

PLEASE CITE THE PUBLISHED VERSION

<https://doi.org/10.1016/j.jmbbm.2019.02.012>

PUBLISHER

© Elsevier

VERSION

AM (Accepted Manuscript)

PUBLISHER STATEMENT

This paper was accepted for publication in the journal Journal of the Mechanical Behavior of Biomedical Materials and the definitive published version is available at <https://doi.org/10.1016/j.jmbbm.2019.02.012>

LICENCE

CC BY-NC-ND 4.0

REPOSITORY RECORD

Smith, James A., Elisa Mele, Rowan Rimington, Andrew Capel, Mark Lewis, Vadim Silberschmidt, and Simin Li. 2019. "Polydimethylsiloxane and Poly(ether) Ether Ketone Functionally Graded Composites for Biomedical Applications". figshare. <https://hdl.handle.net/2134/37094>.

Polydimethylsiloxane and poly(ether) ether ketone functionally graded composites for biomedical applications

James A. Smith¹, Elisa Mele^{2*}, Rowan P. Rimington³, Andrew J. Capel³, Mark P. Lewis³, Vadim V. Silberschmidt¹, Simin Li¹

¹*Wolfson School of Mechanical, Electrical and Manufacturing Engineering, Loughborough University, Loughborough, Leicestershire, LE11 3TU, UK*

²*Department of Materials, Loughborough University, Loughborough, Leicestershire, LE11 3TU, UK*

³*School of Sport, Exercise and Health Sciences, Loughborough University, Loughborough, Leicestershire, LE11 3TU, UK*

* E-mail address: e.mele2@lboro.ac.uk

Abstract

Functionally graded materials (FGMs), with varying spatial, chemical and mechanical gradients (continuous or stepwise), have the potential to mimic heterogenous properties found across biological tissues. They can prevent stress concentrations and retain healthy cellular functions. Here, we show for the first time the fabrication of polydimethylsiloxane and poly(ether) ether ketone (PDMS-PEEK) composites. These were successfully manufactured as a bulk material and functionally graded (stepwise) without the use of hazardous solvents or the need of additives. Chemical, irreversible adhesion between layers (for the FGMs) was achieved without the formation of hard, boundary interfaces. The mechanical properties of PDMS-PEEK FGMs are proven to be further tailorable across the entirety of the build volume, mimicking the transition from soft to harder tissues. The introduction of 20 wt.% PEEK particles into the PDMS matrix resulted in significant rises in the elastic modulus under tensile and compressive loading. Biological and thermal screenings suggested that these composites cause no adverse effects to human fibroblast cell lines and can retain physical state and mass at body temperature, which could make the composites suitable for a range of biomedical applications such as maxillofacial prosthetics, artificial blood vessels and articular cartilage replacement.

Keywords: *polydimethylsiloxane, polyether ether ketone, functionally graded materials, biocompatibility*

1. Introduction

Medical devices, implants and artificial tissues have revolutionised patient healthcare over the past century [1,2]. Fundamentally, their success is reliant upon the combination of patient need, sophisticated design, medical staff preference and structural biomaterials [2]. Biomaterials can be defined as any natural or synthetically engineered substance that can replace or prolong body function beyond its natural capacity [3–6]. Synthetic polymeric biomaterials are used extensively throughout the biomedical industry thanks to a multitude of desirable properties, such as ease of surface modification and device manufacture, biocompatibility, controlled mechanical properties, corrosion resistance, and successful operation at body temperature [5,7–9]. However, trends of disease prevalence and ageing populations are placing huge expectation and demand upon such materials and healthcare providers [10]. Hence, there is need to produce economically enhanced polymeric biomaterials that that closely emulate the mechanical properties of the human body.

Blending of immiscible polymers offers a potential solution to this need [11]. Blending processes are relatively cheap and scalable, and bulk material properties can be fine-tuned for application, by controlling fractional volumes introduced [7]. Most polymer composites, however, require the use of additives or toxic solvents to achieve/enhance miscibility and homogeneity throughout the material with separated phase domains [12]. Such material interfaces act as stress concentrators, leading to a loss in mechanical properties and functionality through delamination [13]. For example, blends of ultra-high molecular weight polyethylene (UHMWPE) and polydimethylsiloxane (PDMS) have been proposed to form transitional implants between articulating and impact absorbing components within acetabular cups [14]. The polymers were mixed under high shear and elevated temperature (180 °C) and a decrease in the elastic modulus was observed by increasing the amount of PDMS within the UHMWPE matrix. Another study reports on blends of polycaprolactone (PCL) and poly(L-lactide-co-ε-caprolactone) (PLC) for the treatment of Patent Ductus Arteriosus (PDA, a common form of congenital heart disease) [15]. PCL/PLC/BaSO₄ solutions (BaSO₄ was added for X-ray fluoroscopy) in dichloromethane were prepared and then cast on glass substrates to obtain films. Residual solvent (which is toxic) was removed by drying the films under vacuum at 37 °C for 7 days. The addition of PLC reduced the elastic modulus of the blends from 175 MPa (for PCL/BaSO₄) to 110 MPa (for blends containing 50% of PLC). PCL

1 was blended also with polylactic acid (PLA) in order to form peripheral nerve conduits [16].
2 Dichloromethane was used to prepare PCL/PLA solutions that were casted to obtain porous films. A
3 washing procedure in NaOH was used in this case to remove solvent residues.

4 Polymer composites can be processed to form functionally graded materials (FGMs) that match the
5 anisotropic mechanical behaviour observed in natural biological tissues [17,18]. FGMs have generated
6 significant interest within the biomedical research community, leading to the fabrication of numerous,
7 multi-material and multi-structural implants and tissue scaffolds [17,19–22]. Such devices are essential
8 for the promotion of normal cellular functions (adhesion, growth, proliferation and differentiation),
9 especially if multiple cell types exist within layers [22–26].

10 This study presents both the development and the stepwise-functional grading of biomedically relevant
11 composites comprised of PDMS and PEEK. Unlike other polymer-blended FGMs for biomedical
12 applications, which typically adopt biodegradable thermoplastics with varying spatial arrangements to
13 alter mechanical performances of scaffolds, the work undertaken utilises a thermoset matrix (PDMS)
14 [27–30]. This promoted the chemical adhesion between complete-graded layers to form a dense
15 structure. The combination of PDMS and PEEK was motivated by their contrasting mechanical
16 properties, which could help to bridge the gap between soft (skin, muscle and cartilage) and connective
17 tissue interfaces. PDMS is a flexible thermoset elastomer with a reported elastic modulus between 0.5-
18 3.0 MPa, rendering it well suited to soft-tissue applications (plastic reconstruction surgery, mammary
19 implants, joint replacement) and medical devices (balloon catheters, artificial heart valves, microfluidic
20 chips) [31–35]. On the contrary, PEEK is a high-performing thermoplastic (elastic modulus of 3-4 GPa),
21 employed within the fields of both trauma care and orthopaedics in the forms of maxillofacial implants,
22 articulation devices, fixation plates and screws, spinal fusion cages, wound dressings, heart valves and
23 pumps, thanks to its good load bearing capacity, chemical resistance and suitability to aggressive
24 sterilization techniques [36–42]. In the literature, the chemical synthesis of PDMS-PEEK copolymer
25 was attempted via the condensation of dimethylamino terminated PDMS and hydroxy terminated PEEK
26 oligomers [43]. The copolymer was intended to be used as impact modifier for the toughening of PEEK.
27 However, its thermo-oxidative instability prevented its application. Here, for the first time, it is shown
28 that PDMS-PEEK can be physically blended without the use of solvents or additives and the resulting

composites can be processed via moulding. In this study, fabrication, material characterisation and mechanical performance are highlighted, as well as cytotoxicity screening of the PDMS-PEEK composites.

2. Materials and Methods

Fabrication of PDMS-PEEK composites

Polydimethylsiloxane ($M_w \sim 60000$ g/mol, Dow Corning® EI-1184 Optical Encapsulant Kit) was purchased from Ellsworth Adhesives Ltd. Poly(ether) ether ketone powder ($M_w \sim 78000$ g/mol, VESTAKEEP® 2000 UFP 20) was purchased from Evonik Industries GmbH (Marl, Germany). All chemicals were used without further purification.

PDMS prepolymer solutions were prepared by combining part A prepolymer (dimethyl siloxane, dimethylvinylsiloxyl-terminated, dimethylvinylated and trimethylated silica) and part B curing agent (dimethylhydrogensiloxyl + catalyst) at a 1:1 ratio. Typically, the catalyst is metal-centred (platinum), which promotes hydrosilylation reactions between terminal vinyl groups found in siloxane (part A) and methylhydrogen siloxane units (part B) [44]. PEEK particles were then introduced into the PDMS solution at 10 (PDMS-PEEK10%) and 20 wt.% (PDMS-PEEK20%). Blends with 30 wt.% and 40 wt.% PEEK particles were also investigated; however, inconsistencies in manufacture were experienced (see supporting information Fig. S1). Each fractional mixture was manually stirred to obtain a uniform dispersion of the PEEK powder. This was identified at the point at which the PEEK powder was unable to be visually separated from the bulk PDMS, forming an opaque, tan-coloured-gel like substance, which increased in viscosity, upon rising PEEK fractional volumes.

The PDMS-PEEK dispersions were placed into a desiccator for ~20 minutes, removing air introduced by mixing. A compressed air gun was used to break the surface tension of any remaining bubbles in the specimens. The PDMS-PEEK mixtures were poured into machined aluminium moulds following ASTM D638-14 (type iv); (gauge length 25.0 mm; width 6.0 mm; thickness 3.2 mm), ASTM D395-16 (type 1^A) compressive set, (Ø 29.5 mm; thickness 12.5 mm) standards and left to cure at 70 °C for 1

hour. Samples were immediately removed from the oven and left to cool at room temperature, prior to testing.

To produce functionally graded specimens, PDMS-PEEK blends of equal volume were built up in a controlled layer-by-layer process. In this case, PDMS-PEEK20% blends were cast first into aluminium moulds similar to ASTM D395-16 (type 1^A) compressive set, (Ø 29.5 mm; thickness 12.5 mm) and left to cure at room temperature for 24 hours. This process was repeated for subsequent PDMS-PEEK10% and PDMS layers. The semi-cured FG specimens were then held at 70 °C for 1 hour to ensure full cure, before being removed from oven and cooled at room temperature. Dimensional accuracy of the attained specimens was assessed with Vernier calliper (Digital 150mm, Duratool).

Morphology and surface characterisation

PEEK particle size was examined with Mastersizer 3000 (Malvern) laser-diffraction particle-size analyser. Both surface and cross-sectional morphologies of the PDMS-PEEK composites were analysed with scanning electron microscopy (TM3030, Hitachi). A 15 nm coating of Au-Pd (80:20 ratio) was deposited onto the samples by sputter coater (Q150T ES, Quorum) prior to SEM inspection.

Chemical and thermal analysis

Energy dispersive X-ray (EDX) analysis of the composites was undertaken to examine their elemental composition (TM3030, Hitachi). Five distinct points were assessed across five individual specimens for each composite. Thermal behaviour of the PDMS-PEEK composites was determined by thermogravimetric analysis (TGA) and differential scanning calorimetry (DSC). Samples with a weight of 10 mg were loaded into designated aluminium pans and exposed to temperatures ranging from 0-400 °C for TGA (Q5000IR, TA Instruments) and from 20-600 °C for DSC (2920, TA Instruments) at a scan rate of 10°C/min in a nitrogen atmosphere.

Mechanical performance

Both uniaxial tensile and compressive tests were performed to characterise the mechanical properties of the PDMS-PEEK blends, using Instron universal testing systems (Instron 3344 and 3363), equipped with 1 kN and 10 kN load cells, respectively. Prior to the tests, a 5 N preload was applied to overcome flexible nature of the tensile specimens, while polytetrafluorethylene (PTFE, WD-40) lubricant was applied to the surfaces between compression plates and specimens to reduce any ‘barrelling’ effect

caused by surface friction. A quasi-static strain rate of 0.001 s^{-1} was applied in both tensile and compressive tests. Specimen failure was identified as a drop-in load of 5%. Five tensile and five compressive pieces were tested for each PDMS-PEEK blend.

Cytotoxicity screening

2.1.1 Cell culture

Human dermal fibroblasts (HDF), all below passage 13 (ATCC), were cultured in T80 flasks (Nunc™, Fisher Scientific, UK) and incubated at 5% CO_2 atmosphere and 37°C (HERA cell 240i, Fisher Scientific, UK) in growth medium (GM), composed of 89% Dulbecco modified Eagle's medium (DMEM, Sigma Aldrich, UK), 10% foetal bovine serum (FBS, Pan Biotech, UK) and 1% penicillin-streptomycin (P/S, Fisher Scientific, UK) until 80% confluence was obtained. Incubated cells GM was changed every 24 h prior to being harvested for experimental use.

2.5.2 Polymer sample preparation

All samples were sterilized with ultra-violet (UV) light for ≥ 1 h, prior to being adhered to culture well plates using an in-house bio-adhesive (aquarium glue) that was found to be biocompatible [45]. Samples were then rinsed with 70% industrial methylated spirit (IMS) solution and left to air-dry prior to being washed with phosphate buffered saline (PBS) solution. Each polymer disc ($\varnothing$ 30 mm; thickness 1 mm; approx. surface area 15 cm^2) provided a surface-area-to-volume ratio of $3 \text{ cm}^2 \text{ mL}$ and was designed to cover most of the culture area of a six-well plate. Where possible, the methodology was devised with the international standards organisation (ISO 10993) guidelines as previously reported [46].

2.5.3 Experimental treatment

When determining the biocompatibility of biomedical materials, interactions between the chemical leachate of such materials and cell cultures must be assessed. Hence, sample discs were used to evaluate the indirect ($n = 1$) biocompatibility of each polymer per repeat ($n = 3$). Experiments generated $n = 3$ per condition, totalling $n = 6$ per analysis at each specific time-point, derived from $n = 3$ experimental repeats. HDF cells were seeded at a density of 10^4 cells per cm^2 on tissue culture plastic within chemically leached medium of each polymer. To obtain this, polymer blend discs were attached to culture wells that remained acellular (containing only medium (denoted "MEDIA ONLY")). Chemically leached medium from each polymer was then transferred to its corresponding experimental well,

ensuring that cellular medium was directly representative of cumulative polymer degradation at each specific time-point. Each MEDIA ONLY well was preincubated with 2 mL GM for 24 h prior to commencing each experiment, to ensure cells were seeded within medium that had been exposed to the chemical leachate of each polymer. Once transferred to experimental wells, acellular wells were replenished with 2mL GM before each subsequent media change. HDF cell viability was determined at 24 h intervals (24, 48 and 72 h), prior to being fixed for morphological analyses at experimental termination time-points (72 h).

2.5.4 Cell viability alamarBlue®

To determine proliferation/viability of HDFs when interacting with polymer composites, alamarBlue® reagent (diluted 1:10 in DMEM containing 1% P/S) was added at 24, 48 and 72 h time-points. Cells were washed twice with 2 mL PBS before being treated with 2 mL per well alamarBlue® stock solution and humidified at 5% CO₂ and 37 °C for 4 h. 100 µL of solution, per well, was then added to a 96-black well plate and analysed for fluorescence intensity. Increased fluorescence of alamarBlue® reagent is indicative of an increase in cellular viability. alamarBlue® fluorescence signal was excited at 540–570 nm (peak excitation: 570 nm) and emitted at 580-610 nm (peak emission: 585 nm).

2.5.5 Immunofluorescence and morphological analyses

At experimental termination time-point (72 h), cells were washed twice in 2 mL PBS per well prior to being fixed in 3.7% paraformaldehyde solution. Once fixed, HDF cell cultures were permeabilised (Triton X-100, Fisher, 1:500) and labelled for cytoskeletal protein F-actin and nuclear DNA using molecular probe rhodamine phalloidin (1:200; Life Technologies, Molecular Probes) and 4',6-diamidino-2-phenylindole (DAPI, 1:2000) for ≥1 h. Fluorescence images were captured using a Leica DM2500 fluorescence microscope (20×) with manufacturer's software (Leica Application Suite X), and analysed using IMAGE J 1.50a/Fiji (Java 1.6.0_24) software (National institute of Health, Bethesda, MD). Image inclusion criteria were set at ≥5 images per well. Nuclei number analysis was performed using an in-house macroinstruction designed for Fiji image analysis software.

Statistical analysis

Both mechanical and cell-viability data sets were statistically analysed with software package (SPSS 24, IBM). 1 x 3 one-way analysis of variance (ANOVA) was undertaken to assess mechanical data that

met parametric assumptions. Where significant observations were met, Tukey *post-hoc* analysis was used to determine differences between sample groups. Where parametric assumptions were violated, non-parametric Welch's ANOVA, followed by Games-Howell *post-hoc* analysis, was used to determine statistical differences between sample groups. A 6 x 3 ANOVA was undertaken to analyse cell viability. One-way ANOVA (1 x 6) was used to analyse the morphological nuclei number concerned with experimental termination time-points. Here, where significant interactions were observed, Bonferroni *post-hoc* analysis was used to assess differences between conditions at specific time-points. Non-parametric Kruskal-Wallis (*H*) analysis was undertaken where data violated parametric assumptions. Mann-Whitney (*U*) tests were then utilised to determine significance between conditions, in accordance with Bonferroni correction to account for incremental type-1 error. All data are reported as mean $\pm$ standard deviation (SD). Significance was assumed at $p < 0.05$.

3. Results and Discussion

3.1 Morphology and surface characterisation

The replica moulding technique was used to fabricate PDMS samples with and without PEEK particles for ease of processing and dimensional accuracy [47]. PDMS samples were optically transparent and completely void of defects despite thicknesses up to 12.5 mm (Fig. 1a). Upon the introduction of PEEK particles, the elastomer became both opaque and tan coloured. Polymer blends became duller and washed out in appearance as PEEK fractional volumes increased (Figs. 1b-c and S1a). The PEEK particles were irregular in morphology, with an average size distribution of 10-50 μm (Fig. 1d). During sample preparation, it was observed that organic solvents were not required to obtain homogenous dispersions of PEEK particles throughout the liquid PDMS prepolymer (an advantage over previous works) [48,49]. This was credited to the low surface tension of the PDMS prepolymer ($\sim 20 \text{ mJ/m}^2$) that promoted the wetting of PEEK particles (surface energy $\sim 50 \text{ mJ/m}^2$) and limited the formation of aggregates [50–52]. The presence of PEEK within the PDMS elastomer had no detrimental effects upon the curing process, which was achieved after 1 hour at 70 $^{\circ}\text{C}$, as for pristine PDMS. Often, solvents are an essential commodity to ensure successful multi-material processing [53]. However, their use in

manufacturing can add significant cost (purchase, recycling and safe disposal) and be detrimental to both animal models and the environment [54]. Hence, the materials here developed were completely solvent-free to ensure biocompatibility and alleviate cytotoxicity [53]. SEM analysis of the obtained composites (surfacing facing the mould, bottom) revealed a smooth surface finish for the PDMS control sample (Fig. 1e) and enhanced surface roughness for PDMS-PEEK10% (Fig. 1f) and PDMS-PEEK20% (Fig. 1g). The increase in surface roughness is attributed to semi-embedded PEEK particles, forming protrusions and craters (blue arrows in Figs. 1f and 1g) across the composite surfaces. PEEK particles were uniformly distributed throughout the sample and, as expected, their density increased with fractional PEEK volume. Observations drawn from sample cross sections also indicated significant PEEK homogeneity throughout the PDMS matrix for PDMS-PEEK10% and PDMS-PEEK20% (Fig. 1h-1j). During the cross-linking process, the PEEK particles remained homogeneously distributed within the PDMS matrix without precipitation or aggregation at the bottom of the mould, prompting desirable manufacturability and consistency.

Cavities (red dashed boxes in Figs. 1i and 1j) existing within the cross-sectional area of the PDMS-PEEK10% and PDMS-PEEK20% are attributed to directional shear forces applied by a scalpel blade during samples preparation for SEM imaging. The cutting force caused the delamination of loosely bound PEEK particles from their PDMS matrix. This demonstrates that the liquid PDMS prepolymer coated the surface of each single PEEK particle (during PDMS and PEEK mixing) and broke down aggregates in the PEEK powder without need of solvents or high shear mixing procedures.

Fig. 1. Photographs of bulk specimens; PDMS (a), PDMS-PEEK10% (b), and PDMS-PEEK20% (c). Surface morphology (SEM) of PEEK particles (d), PDMS (e), PDMS-PEEK10% (f) and PDMS-PEEK20% (g). Cross sectional morphology (SEM) of PDMS (h), PDMS-PEEK10% (i) and PDMS-PEEK20% (j). Arrows (blue) indicate surface protrusions and craters on composite surface. Cavities (red dashed boxes) formed during sample preparation for imaging.

1

2

3.2 Chemical and thermal analysis

EDX analysis was performed across the surface of PDMS, PDMS-PEEK10% and PDMS-PEEK20% as well as a PEEK reference, to determine elemental composition, and, in turn, ensure both the validity of supplied materials and batch quality of the specimens (Fig. S2). Both silicon and oxygen are fundamental constituents of PDMS and, hence, found in abundance in the PDMS control and the PDMS-PEEK blends. As expected, silicon slightly declined as fractional volumes of PEEK increased, indicating that PEEK particles were partially exposed at the surface. The minimal rise in oxygen was attributed to the introduction of the PEEK, which was found bound to carbon throughout its structure. A gradual rise in carbon was witnessed with increasing fractions of PEEK, as it is the primary constituent of PEEK's chemical skeleton.

The thermal properties of the PDMS-PEEK composites were investigated because thermal stability and mass retention at body (37°C) and sterilisation temperatures (121°C) are prerequisites for the fabrication of structural implants and functional biomedical devices [55]. TGA showed that the PDMS and PDMS-PEEK composites were stable across a broad range of temperatures (Fig. 2a and S3a). Between 37-200°C, negligible mass loss was experienced by all polymer samples. As temperatures approached 300°C, the masses retained for PDMS, PDMS-PEEK10%, PDMS-PEEK20% and PEEK were all higher than 98.5%. The mass retained for PEEK stayed consistent (99%) as temperatures rose to 500°C, while significant mass reduction was observed for PDMS (-21%), PDMS-PEEK10% (-17%) and PDMS-PEEK20% (-13%) compared to mass at room temperature, which is inversely correlated to PEEK fractional volume. The corresponding mass losses observed between 400-500 °C are indicative of the thermal 'unzip-degradation' depolymerization of PDMS, resulting in the cleavage of Si-O-Si bonds and the subsequent formation of cyclic siloxanes of varying chain lengths [56,57]. The increased retention of mass observed for PDMS-PEEK10% and PDMS-PEEK20% against the PDMS control is attributed to the higher specific heat capacity of the PEEK fraction. As PEEK inclusions increased and the distance between adjacent particles declined, higher thermal tolerances were achieved throughout the matrix. Due to the chemical stability of PEEKs aromatic backbone, degradation of the polymer was not witnessed between 400-500°C [58–60]. At 600°C, mass retention for all samples demonstrated a sharp drop, with PDMS, PDMS-PEEK10%, PDMS-PEEK20% and PEEK retaining final masses of 46%,

42%, 62% and 65%, respectively. Of all the polymers, PEEK was most thermally stable (degradation temperature $\sim 550^\circ\text{C}$), consistent with the existing literature [60,61]. As temperatures surpassed 500°C , PDMS and its composites experienced further mass loss due to thermal ‘rearrangement-degradation,’ promoting, in turn, the rearrangement of Si-O-Si bonds and the heterolytic cleavage of Si-CH₃ bonds, to form methane and additional cyclic oligomers [62,63]. Between $500\text{--}600^\circ\text{C}$, thermal degradation of PEEK was initiated, with the associated mass loss attributed to the random cleavage of ether and ketone groups linking the aromatic rings together [60]. It was reported that beyond 650°C carbonyl groups are cleaved, forming radical decomposition intermediates such as phenols, dibenzofuran, CO, CO₂ and carbonaceous char [60,64,65].

In Figure 2b and S3b, distinct peaks indicating melting temperature (T_m) are witnessed at 350°C for PDMS-PEEK10%, PDMS-PEEK20% and PEEK. A T_m peak for PDMS is not observed due to its step change occurring at a reported -40°C [66]. A step change, indicative of glass transition temperature (T_g), was observed at 140°C in PEEK (Fig. 2b), consistent with previous findings; however, this became less prominent (reduction in area under the curve) as fractional volume of PEEK declined to 20 wt.% [67,68]. PDMS’s T_g was previously reported between -115 to -125°C [66,69,70]. The obtained TGA and DSC data suggest that the PDMS-PEEK composites have the capacity to retain mass and phase well beyond body and sterilisations temperatures and, hence, are suitable for biomedical applications.

Fig. 2. TGA (a) and DSC (b) of PDMS, PDMS-PEEK10%, PDMS-PEEK20% and PEEK samples.

3.3 Mechanical performance

The mechanical properties of the PDMS-PEEK composites were evaluated in both tension and compression (Fig. 3). All samples exhibited stress-strain behaviour that are typical of PDMS-based materials, i.e. a period of linearity, followed by non-linearity and then subsequent ultimate failure (Fig. 3a) [71–73]. The modulus of toughness U_t (calculated as the area under the graph) for both tensile and compressive specimens was recorded. PDMS exhibited a U_t of 0.7 ± 0.2 MPa (tension) and 2.1 ± 0.4 MPa (compression). The addition of PEEK fractional volumes saw a rise in toughness across all the PDMS-PEEK composites. In tension the inclusion of 10 wt% and 20 wt% PEEK determines a 1.1-fold increase over the control (0.8 ± 0.1 MPa for PDMS-PEEK10% and 0.7 ± 0.2 MPa for PDMS-PEEK20%). Compared to PDMS, PDMS-PEEK10% and PDMS-PEEK20% saw 1.6-fold (3.3 ± 0.4 MPa) and 2.1-fold (4.4 ± 0.2 MPa) increases, respectively.

In tension (Fig. 3b, top quadrant), the elastic modulus (calculated for a strain interval between 10-20% in the linear region of the curve) obtained for the PDMS control sample was 0.95 ± 0.03 MPa, in agreement with previous studies on PDMS-based materials [35,72,74]. The addition of PEEK determined statistical rises ($p < 0.05$) in the elastic modulus for both PDMS-PEEK10% (1.40 ± 0.15 MPa) and PDMS-PEEK20% (3.68 ± 0.59 MPa), corresponding to a 1.5-fold (PDMS-PEEK10%) and 3.9-fold increase (PDMS-PEEK20%) compared to the PDMS control, respectively. Under compressive load (Fig. 3b, bottom quadrant), the elastic moduli recorded for PDMS-PEEK10% and PDMS-PEEK20% were 1.80 ± 0.32 MPa and 4.22 ± 0.32 MPa, respectively. In this case, 1.2-fold and 2.9-fold increases were achieved over the PDMS control (1.46 ± 0.45 MPa) by the incorporation of 10 and 20 wt.% PEEK into the elastomeric matrix. Statistical significance was observed between PDMS and PDMS- PEEK20%, and PDMS-PEEK10% and PDMS-PEEK20% but not between PDMS and PDMS-PEEK10%. PDMS specimens (Fig. 3c, top quadrant) exhibited a peak stress of 1.14 ± 0.35 MPa in tension, whereas values of 1.42 ± 0.16 MPa (1.2-fold) and 1.57 ± 0.2 MPa (1.4-fold) were recorded upon the introduction of 10 wt.% and 20 wt.% PEEK, respectively, with no statistical significance ($p > 0.05$) observed between groups. In compression (Fig. 3c, bottom quadrant), the peak stresses of all respective groups were significantly different ($p < 0.05$) from each other. Peak stress values were recorded as were 5.53 ± 0.41 MPa (PDMS), 8.92 ± 1.15 MPa (PDMS-PEEK10%) and 13.27 ± 1.78 MPa (PDMS-PEEK20%), corresponding to 1.6-fold and 2.4-fold increases over PDMS, respectively.

Fig. 3. Engineering stress/strain curve (a), elastic moduli (b) and peak stress (c) for PDMS (green), PDMS-PEEK10% (red) and PDMS-PEEK20% (blue). Samples in; tension (top) and compression (bottom). *Statistical significance ($p < 0.05$) and **no-statistical significance ($p > 0.05$) observed compared to PDMS control.

1

2

Evidently, the incorporation of PEEK into the PDMS matrix had a significant impact on the mechanical performance of the polymer composite. Typically, the polymers utilised as the matrix are ‘state-of-the-art’ with a designated application (PEEK for orthopaedic devices; UHMWPE for articulating femoral heads and PDMS for soft tissues) and the fillers act to enhance or change a specific property (mechanical, thermal, biocompatibility, etc.) [75]. Hence, it seemed appropriate to compare these novel PDMS-PEEK materials to existing biomedical composites, specifically those with a PDMS matrix (Table 1). For PDMS-HA composites, the elastic modulus was reported as 0.7 ± 0.2 MPa (10 wt.% HA) and 0.7 ± 0.3 (20 wt.% HA), which is a 1.1-fold and 1.2-fold increase over their control [76]. Here, 1.5-fold and 3.9-fold increase in the elastic modulus are reported for PDMS-PEEK10% and PDMS-PEEK20%, respectively, in relation to PDMS. The ultimate tensile strength was 2.0 ± 0.2 MPa and 2.2 ± 0.6 MPa for PDMS-HA10% and PDMS-HA20%, respectively, correlating to 1.0-fold and 2.3-fold increases over the control [76]. For the PDMS-PEEK blends, 1.4 ± 0.2 MPa (PDMS-PEEK10%) and 1.6 ± 0.2 MPa (PDMS-PEEK20%), which equate to 1.2-fold and 1.4-fold increases over PDMS, were obtained. Increased levels of elongation were also observed for PDMS-HA10%, PDMS-HA20%, PDMS-Polytetrafluoroethylene (PTFE) 10% and PDMS-PTFE20% [77]. This trend was initially witnessed in PDMS-PEEK10%, however for PDMS-PEEK20% elongation at break decreased, following the trends of Polyurethane (PU)-UHMWPE [78].

The divergence between tensile and compressive peak stresses among different groups can be attributed to both the intrinsic properties of the composite polymers and differences in deformation mechanism experienced by materials under load. PDMS’ structure is comprised of both cross-linked (covalently bonded) polymer chains (forming a 3D network) and loosely bound (Van der Waals’) entangled, amorphous chains (Fig. 4a.i) [82]. As tensile load is applied to the elastomers (above their T_g), the secondary bonds holding the chains together break, enabling them to slide past one another reversibly within the linear region (load carrying capacity matches deformation rate) [82]. In turn, these chains align and re-orientate themselves parallel to the direction of loading (Fig. 4a.ii) [83]. As greater number of polymer chains align and stretch (to absorb energy), irreversible plastic deformation occurs, exhibited by a small but distinctive toe region in the stress-strain curve [84]. In attempt to dissipate stress, the chemical backbone rotates until bond dislocation occurs, creating micro-cavitation, leading to failure

(Fig. 4a.iii) [83–85]. In comparison, compressive PDMS specimens (Fig. 4b.i) experience similar chain sliding as in tension; however, the entangled chains become interpenetrated with one another reducing molecular mobility and increasing polymer stiffness at lower strain magnitude (Fig. 4b.ii) [86]. As the re-orientation and superimposed polymer entanglement is passive (due to lateral contraction), the stress-strain curve exhibited a clear heel region at relative higher strain magnitude. The subsequent increase of the stress-strain curve is result of interlocked polymer deformation, until covalent bond breakage leads to buckling and rupture (Fig. 4b.iii) [87].

By introducing PEEK into the elastomeric matrix, stiffness increased as a function of particle loading (up to 20 wt.%). Rationale for this increase in stiffness is attributed to the higher concentration of PEEK particles, restricting chain mobility and the higher intrinsic properties of the particles compared to PDMS [88–90]. Consequently, higher loading was necessary to plastically deform the PDMS-PEEK composites in both tension and compression, correlating with the higher elastic moduli observed. After achieving peak stress, the process of PEEK particle detachment from the PDMS matrix ensued, leading to voids and rupture in tension. Under compressive loading, the distance between bound PEEK particles decreases with load, resulting in material consolidation [89]. After peak stress, the bound elastomer was stripped away from the bound PEEK particles, generating voids that are unable to dissipate the applied stress. Elongation at break recorded for PDMS, PDMS-PEEK10% and PDMS-PEEK20% were $189.2 \pm 13.1\%$, $191.7 \pm 6.0\%$ and $180.7 \pm 15.3\%$ in tension, respectively (Fig. 4c, top quadrant), and $31.1 \pm 9.5\%$, $25 \pm 3.3\%$ and $39.0 \pm 2.1\%$ in compression (Fig. 4c, bottom quadrant), respectively. The results reported for PDMS agreed with previous findings [35,74]. It is understood that the levels of elongation at break can be controlled by the fraction of particle filler as well as curing temperature and level of cross-linker [71,74,89]. Recent examples of such behaviour include the addition of starch and cocoa shell to PDMS (for biodegradable packaging) which caused a 10-fold and 68-fold reduction in elongation at break [49,91].

Importantly, in this study, the addition of PEEK particles into the PDMS elastomer did not affect sample's elongation at break significantly ($p > 0.05$). The ability of the PDMS-PEEK samples to retain similar levels of ductility, yet increase their load-bearing capacity is considered highly advantageous compared with previous works [49,91]. Hence, these polymer composites could be adopted for a far

greater range of soft-tissue engineering applications. One example of note is the field of maxillofacial
prosthetics. Unlike commercial elastomers reported in literature, the tensile properties obtained from
PDMS-PEEK10% (1.40 ± 0.15 MPa) composites are far more representative of submandibular tissue
(1.28 ± 0.06 MPa) [92,93]. It is understood that skin possesses age-dependent biomechanical properties,
and as such, the PDMS-PEEK composites could be tailored to match the mechanical properties of tissue
as a function of time [94]. Further applications could include prosthetic blood vessels (saphenous vein
and arterial walls) and articular cartilage, as the elastic moduli for the PDMS-PEEK composites are
within the reported range [25].

1 **Table 1.** Composition and mechanical parameters of biomedical composites with PDMS matrix (RT – room temperature, CS – crosshead speed).

Composites	Volume fraction (wt.%)	Elastic modulus (MPa)	Ultimate tensile strength (MPa)	Elongation at break (%)	Sample preparation	Test parameters	Ref.
UHMWPE-PDMS	0	34	-	-	Shear mixed (100 rpm at 180°C), compression moulding (160°C)	Tensile CS = 50 mm/min	[14]
	10	32	-	-			
	20	26	-	-			
	30	11	-	-			
PDMS-HA	0	0.63	1.97	525	Two-roll mixer, hot compression moulding (185°C for 35 min)	Tensile RT CS = 30 mm /min	[76]
	10	0.70	1.98	529			
	15	0.72	2.14	532			
	20	0.76	2.25	529			
	25	0.87	2.26	516			
	30	3.23	1.46	235			
PDMS-PTFE	0	-	0.70	275	Solvent casting with magnetic stirrer (3 hrs)	Tensile	[77]
	10	-	0.95	440			
	20	-	1.30	550			
	30	-	1.40	560			
PU-UHMWPE	0	17	48	435	Powders dried (80-90°C for 12 h) Melt blended, twin screwed (160 rpm at 225-235°C)	Tensile RT	[78]
	5	23	38	375			
	10	25	36	350			
	15	24	30	330			
	20	32.5	23	275			
	25	36	19	235			
	30	38	15	180			
UHMWPE-PEEK	0	700	48	-	Rotary ball milled (300 rpm for 1hr), cold compression moulded (100 Kg/cm ²) and temperature raised and held 0-200°C) and held (1hr)	Tensile RT CS = 25 mm/min	[79]
	3	1100	30	425			
	6	1000	20	225			
	9	900	20	100			
	12	800	17	90			
	15	750	15	20			
PEEK-PTFE	7.5	1500	784	11.2	Melt blended, twin-screwed (330-350°C)	Tensile	[80]
	15	1430	77	10.5			
	22.5	1320	70	10.4			
	30	1230	64.6	8.9			

PEEK-HA	0	3000	100	-	Shear mixed (40 rpm at 360°C), blends granulated and dried (160°C for 2 hrs), injection moulded (14 MPa at 340-395°C at 30 rpm) into mould (50°C), annealed (245°C for 2 hrs).	Tensile 100 kN load-cell CS = 1 mm/min	[81]
	10	3500	95	-			
	20	4000	70	-			
	30	8000	65	-			
PDMS-PEEK	0	0.95	1.14	189.18	2-part PDMS shear mixed (1:1 ratio) + PEEK. Desiccated (~20 min) and air blasted. Moulded and cured (70°C)	Tensile 1 kN + 5 N preload $\dot{\epsilon} = 0.001 \text{ s}^{-1}$	This study
	10	1.4	1.42	191.7			
	20	3.68	1.57	180.74			

1

2

3

4

5

Fig. 4. Schematic of PDMS in; tension (a) and compression (b). Elongation at break (c) for PDMS (green), PDMS-PEEK10% and PDMS-PEEK20% (blue). Samples in; tension (top) and compression (bottom). **No-statistical significance ($p > 0.05$) observed compared to PDMS control.

3.4 Functional grading

Over recent years there has been extensive research surrounding the development of FGMs and FG structures as well as the benefits they can offer to the development of biomedical implants, devices and pharmaceuticals [21,95–97]. Such examples include the blending of acrylates and methacrylates (at varying ratios) in attempt to replicate tissues of intervertebral disks [98]; the fabrication of polycaprolactone (PCL) and β -tricalcium phosphate (β -TCP) porous and dense implants to promote bone regrowth and counter osteonecrosis of femoral heads [99], and the manufacture of functionally graded fixation plates to reduce stress shielding effects observed between cortical bone and metallic implants [100]. Hence, it is of great biomedical significance to assess the feasibility of functional grading of PDMS-PEEK blends and identify their suitability for biomedical application.

After the production and characterisation of the PDMS and PDMS-PEEK composites, functionally graded specimens comprised of all three sample materials were manufactured sequentially with equally measured volumes (Fig. 5a). Compression testing was performed on the functionally graded specimens to determine both their mechanical robustness (compared to that of bulk specimens) and failure mechanism (Fig. 5b). The functionally graded samples followed a comparable stress/strain behaviour to that of bulk PDMS and PDMS-PEEK composites. The effective elastic modulus (also taken for strains between 10-20%) for the FGM specimens was 1.98 ± 0.21 MPa, which exceeded that of PDMS (1.57-fold) and matched that of PDMS-PEEK10%. It was reported that FGMs in compression followed similar stress/strain behaviour within the linear regions as non-graded materials of similar chemical composition, which is true of the PDMS-PEEK composites [98]. However, beyond the linear regions, mechanical failure ensued much earlier, which was also the case for the PDMS-PEEK20% composites [98]. Peak stress and elongation at break were calculated at 4.81 ± 2.0 MPa and $62.4 \pm 0.08\%$, respectively, far closer to those of bulk PDMS and PDMS-PEEK20%. Similarly, both trends (reductions in peak stress and elongation at break) were observed in the compression of FGM intervertebral disks compared to non-FGM specimens (of similar chemical composition) [98].

SEM analysis of post-test specimens suggested that hard interfaces (white dashed lines in Figs. 5c-5f) did not exist between PDMS, PDMS-PEEK10% and PDMS-PEEK20%, supporting high adhesion between the transitional interfaces (Figs. 5c and 5d). Transitions between layers were only identifiable

1 by the increased concentration of PEEK particles. Therefore, the used layer deposition technique
2 allowed the fabrication of monolithic functionally graded structures with PEEK particle densities up to
3 20 wt.%. SEM images also revealed that site failure did not specifically occur at the material interfaces
4 (black dashed box in Fig. 5e and 5f,) indicating the potential to produce FGMs with good load-transfer
5 capacity. Under compressive loads, failure occurred at regions with prominent PEEK particle
6 agglomeration (Figs. 5d and 5f, yellow dashed box). These sites are characterised by significantly lower
7 amounts of elastomer holding the adjacent particles together. Hence, upon the application of load
8 (higher than 4.8 ± 2.0 MPa), these regions acted as stress concentrators, resulting in micro-cavitation that
9 led to particle delamination from the matrix and, ultimately, material rupture [89]. Applications of such
10 functionally graded PDMS-PEEK composites could include multi-material, maxilla-facial prosthesis.
11 Whereby, PDMS and the composite variants aid to replace soft skin-tissue and cartilage, respectively
12 (as the load required to cause delamination/fracture exceeds that of tissues they aim to
13 replace)[92,93,101].

Fig.5. Schematic (left) and photograph (right) of functionally graded PDMS-PEEK composites, ranging from PDMS (top), PDMS-PEEK10% (middle) and PDMS-PEEK20% (bottom) (a). Engineering stress/strain curves for functionally graded PDMS-PEEK samples in compression (b). SEM images of PDMS to PDMS-PEEK10% (c) and PDMS-PEEK10% to PDMS-PEEK20% (d) before compression. SEM images of PDMS to PDMS-PEEK10% (e) and PDMS-PEEK10% to PDMS-PEEK20% (f) after compression.

1
2
3
4
5
6
7
8
9

3.5 Cytotoxicity screening

The cytotoxicity of the PDMS-PEEK composites was assessed *in vitro* using human dermal fibroblast (HDF) population. HDF cell lines were selected based on their proven role in wound healing and tissue repair, as well as, their use with other biomedically relevant polymer composites [14,102–105]. Over the course of 72 hours, exponential growth was witnessed across the cell population (Fig. 6a and S4a) and HDFs showed healthy morphology with spindle-shaped cytoskeletons (red) and flat oval nuclei (blue) (Fig. 6b-6f and S4b). There appeared no morphological change in both the cytoskeleton and nuclei of the HDFs when exposed to the various composites, which agrees with results obtained for pure PEEK specimens [103]. Statistical analysis revealed no significant changes ($p>0.05$) between the polymer composites and control, also in terms of nuclei number per observation field (Fig. 6g and S4c). This suggests that the polymers did not cause any adverse effects on the cell line. PDMS-PEEK blends offered equivalent biocompatibility to that of their constituents and are therefore of interest for soft tissue engineering [106,107].

4. Conclusions

FGMs have the capacity to mimic the natural anisotropy of the human body thus allowing potential development of implants/devices with better mechanical and biological resemblance of the tissues they aim to repair/replace. In this study, biomedically relevant polymer composites were constructed from PDMS and PEEK and functionally graded up to 20 wt.% PEEK particles without the use of solvents. Thermal, mechanical and biological screening of the novel polymer composites revealed their advantages;

- Negligible mass loss at both body (37°C) and sterilization temperatures (121°C)
- Tailorable elastic moduli and high levels of deformation prior to failure
- Functionally graded bulk specimens without the formation of hard interfaces between material layers

- No adverse effects regarding proliferation or morphology of HDF cells, when exposed to polymer leachate.

The fabrication of PDMS-PEEK composites coupled with additive manufacturing technologies could have the capacity to generate functionally graded implants/devices bridging the gap between soft tissues such as; skin, blood vessels and cartilage.

Acknowledgements

Funding: The authors would like to thank: the Engineering and Physical Sciences Research Council (EPSRC) Centre for Doctoral Training in Additive Manufacturing and 3D Printing (EP/L01534X/1) for funding, and the EPSRC grant EP/L02067X/1; the support of the National Institute for Health Research (NIHR), Grant STWK-014; the Additive Manufacturing Research Group at Loughborough University for valuable discussions and equipment. EM acknowledges the support of the Royal Society, Grant RG170174.

1

2

Fig. 6. Cellular viability of HDFs cultured indirectly in polymer chemical leachate and respective controls after 72 h in GM (a). Morphological staining of actin cytoskeleton (red) and nucleic DNA (blue) for HDFs cultured indirectly in polymer chemical leachate and respective controls after 72 h in GM for control (b), PDMS (c), PDMS-PEEK10% (d), PDMS-PEEK20% (e) and PEEK (f). Nuclei per observation field for HDFs cultured indirectly in polymer leachate and respective controls after 72 h in GM (g). *Statistical significance ($p < 0.05$) and **no-statistical significance ($p > 0.05$) observed compared to control. Arrows (white) indicate loose PEEK particles present in leachate.

References

- [1] Ratner, BD, Bryant, SJ, 2004. Biomaterials: Where we have been and where we are going. *Annu. Rev. Biomed. Eng.* 6: 41-75. doi:10.1146/annurev.bioeng.6.040803.140027.
- [2] Joung, YH, 2013. Development of implantable medical devices: from an engineering perspective. *Int. Neurourol. J.* 17: 98. doi:10.5213/inj.2013.17.3.98.
- [3] Williams, DF, 1986. Definitions in biomaterials: Proceedings of a Consensus Conference of the European Society for Biomaterials, Chester, England.
- [4] Williams, DF, 2009. On the nature of biomaterials. *Biomater.* 30: 5897–5909. doi:10.1016/j.biomaterials.2009.07.027.
- [5] Teo, AJT, Mishra, A, Park, I, Kim, YJ, Park, WT, Yoon YJ, 2016. Polymeric biomaterials for medical implants and devices. *ACS Biomater. Sci. Eng.* 2: 454–472. doi:10.1021/acsbiomaterials.5b00429.
- [6] Mao, D, Li, Q, Li, D, Tan, Y, Che, Q, 2018. 3D porous poly(ϵ -caprolactone)/58S bioactive glass–sodium alginate/gelatin hybrid scaffolds prepared by a modified melt molding method for bone tissue engineering. *Mater. Des.* 160: 1–8. doi:doi.org/10.1016/j.matdes.2018.08.062.
- [7] Utracki, LA, 2003. Introduction to Polymer Blends, *Polymer Blends Handbook*. Springer, New York. 1–122. doi:10.1007/0-306-48244-4_1.
- [8] Patel, N, Gohil, P, 2012. A review on biomaterials: scope, applications & human anatomy significance. *Int. J. Emerg. Technol. Adv. Eng.* 2: 91–101.
- [9] Maitz, MF, 2015. Applications of synthetic polymers in clinical medicine, *Biosur and Biotribol.* 1: 161–176. doi:10.1016/j.bsbt.2015.08.002.
- [10] Howdon, D, Rice, N, 2018. Health care expenditures, age, proximity to death and morbidity: Implications for an ageing population. *J. Health Econ.* 57: 60-74. doi:10.1016/j.jhealeco.2017.11.001.
- [11] Sionkowska, A, 2011. Current research on the blends of natural and synthetic polymers as new biomaterials: Review, *Prog. Polym. Sci.* 36: 1254–1276. doi:10.1016/j.progpolymsci.2011.05.003.
- [12] Yang, Z, K, Nollenberger, Albers, J, Craig, D, Qi, S, 2013. Microstructure of an immiscible polymer blend and its stabilization effect on amorphous solid dispersions, *Mol. Pharm.* 10: 2767-2780. doi:10.1021/mp400209w.
- [13] Wang, SS, 1983. Fracture Mechanics for Delamination Problems in Composite Materials, *J. Compos. Mater.* 17: 210–223. doi:10.1177/002199838301700302.
- [14] Khorasani, MT, Zaghayan M, Mirzadeh H, 2005. Ultra high molecular weight polyethylene and polydimethylsiloxane blend as acetabular cup material. *Colloids. Surf. B.* 41: 169-174. doi:10.1016/j.colsurfb.2004.12.007.
- [15] Huang, Y, Wong, YS, Wu, J, Kong, JF, Chan, JN, Khanolkar, L, Rao, DP, Boey, FYC, Venkatraman, SS, 2014. The mechanical behavior and biocompatibility of polymer blends for Patent Ductus Arteriosus (PDA) occlusion device. *J. Mech. Behav. Biomed. Mater.* 36: 143-160. doi:10.1016/j.jmbbm.2014.04.012.
- [16] Sun, M, Kingham, PJ, Reid, AJ, Armstrong, SJ, Terenghi G, Downes S, 2010. In vitro and in vivo testing of novel ultrathin PCL and PCL/PLA blend films as peripheral nerve conduit. *J. Biomed. Mater. Res. Part A.* 93: 1470-81. doi:10.1002/jbm.a.32681.
- [17] Sola, A, Bellucci, D, Cannillo, V, 2016. Functionally graded materials for orthopedic

- applications – an update on design and manufacturing. *Biotechnol. Adv.* 34: 504–531.
doi:10.1016/j.biotechadv.2015.12.013.
- [18] Li, S, Demirci, E, Silberschmidt, VV, 2013. Variability and anisotropy of mechanical behavior of cortical bone in tension and compression. *J. Mech. Behav. Biomed. Mater.* 21: 109-120.
doi:10.1016/j.jmbbm.2013.02.021.
- [19] Kieback, B, Neubrand, A, Riedel, H, 2003. Processing techniques for functionally graded materials. *Mater. Sci. Eng. A.* 362: 81–105. doi:10.1016/S0921-5093(03)00578-1.
- [20] Pompe, W, Worch, H, Epple, M, Freiess, W, Gelinsky, M, Greil, P, Hempel, U, Scharnweber, D, Schulte, K, 2003. Functionally graded materials for biomedical applications. *Mater. Sci. Eng. A.* 362: 40–60. doi:10.1016/S0921-5093(03)00580-X.
- [21] Watari, F, Yokoyama, A, Omori, M, Hirai, T, Kondo, H, Uo, M, Kawasaki, T, 2004. Biocompatibility of materials and development to functionally graded implant for bio-medical application. *Compos. Sci. Technol.* 64: 893–908. doi:10.1016/j.compscitech.2003.09.005.
- [22] Leong, KF, Chua, CK, Sudarmadji, N, Yeong, WY, 2008. Engineering functionally graded tissue engineering scaffolds. *J. Mech. Behav. Biomed. Mater.* 1: 140–152.
doi:10.1016/j.jmbbm.2007.11.002.
- [23] Engler, AJ, Sen, S, Sweeney, HL, Discher, DE, 2006. Matrix elasticity directs stem cell lineage specification. *Cell.* 126: 677-689. doi:10.1016/j.cell.2006.06.044.
- [24] Bracaglia, LG, Smith, BT, Watson, E, Arumugasaamy, N, Mikos, AG, Fisher, JP, 2017. 3D printing for the design and fabrication of polymer-based gradient scaffolds. *Acta Biomater.* 56: 3–13. doi:10.1016/j.actbio.2017.03.030.
- [25] Nemir, S, West, JL, 2010. Synthetic materials in the study of cell response to substrate rigidity. *Ann. Biomed. Mater.* 38: 2-20. doi:10.1007/s10439-009-9811-1
- [26] Vannozzi, L, Ricotti, L, Santaniello, T, Terencio, T, Oropesa- Nunez, R, Canale, C, Borghi, F, Mencias, A, Lenardi, C, Gerges L, 2017. 3D porous polyurethanes featured by different mechanical properties: Characterisation and interaction with skeletal muscle cells. *J.Mech.Behav.Biomed.Mater.* 75: 147-159. doi:10.1016/j.jmbbm.2017.07.0
- [27] Woodfield, TBF, Van Blitterswijk, CA, De Wijn, J, Sims, TJ, Hollander, AP, Riesle, J, (2005). Polymer Scaffolds Fabricated with Pore-Size Gradients as a Model for Studying the Zonal Organization within Tissue-Engineered Cartilage Constructs. *Tissue Eng.* 11: 1297-1311.
doi:10.1089/ten.2005.11.1297.
- [28] Liao, S, Wang, W, Uo, M, Ohkawa, S, Akasaka, T, Tamura, K, Cui, F, Watari, F, (2005). A three-layered nano-carbonated hydroxyapatite/collagen/PLGA composite membrane for guided tissue regeneration. *Biomater.* 26: 7564-7571. doi:10.1016/j.biomaterials.2005.05.050.
- [29] Dávila, JL, Freitas, MS, Inforçatti Neto, P, Silveira ZC, Silva, JVL, D'Ávila MA, (2016) Fabrication of PCL/ β -TCP scaffolds by 3D mini-screw extrusion printing. *J. Appl. Polym. Sci.* 133: 1-9. doi:10.1002/app.43031.
- [30] Converse, GL, Conrad, TL, Roeder RK, 2009. Mechanical properties of hydroxyapatite whisker reinforced polyetherketoneketone composite scaffolds. *J. Mech. Behav. Biomed. Mater.* 2: 627-635.
- [31] Owens, M, 2001. *Elastomers: Siloxane*, Elsevier, Amsterdam. doi:10.1016/B0-08-043152-6/00448-4.
- [32] Kumbar, S, Laurencin, C, Deng, M, 2014. *Natural and Synthetic Biomedical Polymers*. Elsevier, Amsterdam. doi:10.1016/C2011-0-07330-1.
- [33] Abbasi, F, Mirzadeh, H, Katbab, AA, 2001. Modification of polysiloxane polymers for

- biomedical applications: A review. *Polym. Int.* 50: 1279–1287. doi:10.1002/pi.783.
- [34] Park, JH, Park, KD, Bae, YH, 1999. PDMS-based polyurethanes with MPEG grafts: Synthesis, characterization and platelet adhesion study. *Biomater.* 20: 943–953. doi:10.1016/S0142-9612(98)00250-6.
- [35] Schneider, F, Draheim, J, Kamberger, R, Wallrabe, U, 2009. Process and material properties of polydimethylsiloxane (PDMS) for optical MEMS. *Sensors Actuators, A Phys.* 151: 95–99. doi:10.1016/j.sna.2009.01.026.
- [36] Rae, PJ, Brown, EN, Orler, EB, 2007. The mechanical properties of poly(ether-ether-ketone) (PEEK) with emphasis on the large compressive strain response. *Polymer.* 48: 598–615. doi:10.1016/j.polymer.2006.11.032.
- [37] Kurtz, SM, Devine, JN, 2007. PEEK biomaterials in trauma, orthopedic, and spinal implants. *Biomater.* 28: 4845–4869. doi:10.1016/j.biomaterials.2007.07.013.
- [38] Yang, C, Tian, X, Li, D, Cao, Y, Zhao, F, Shi, C, 2017. Influence of thermal processing conditions in 3D printing on the crystallinity and mechanical properties of PEEK material. *J. Mater. Process. Technol.* 248: 1–7. doi:10.1016/j.jmatprotec.2017.04.027.
- [39] Abu Bakar, MS, Cheng, MHW, Tang, SM, Yu, SC, Liao, K, Tan, CT, Khor, KA, Cheang, P, 2003. Tensile properties, tension-tension fatigue and biological response of polyetheretherketone-hydroxyapatite composites for load-bearing orthopedic implants. *Biomater.* 24: 2245–2250. doi:10.1016/S0142-9612(03)00028-0.
- [40] Du, W, Zhang, Z, Fan, W, Gao, W, Sui, H, Li, Z, 2018. Fabrication and evaluation of polydimethylsiloxane modified gelatin/silicone rubber asymmetric bilayer membrane with porous structure. *Mater. Des.* 158: 28–38. Doi:10.1016/j.matdes.2018.08.017
- [41] Arif, MF, Kumar, S, Varadarajan, KM, Cantwell, WJ, 2018. Performance of biocompatible PEEK processed by fused deposition additive manufacturing. *Mater. Des.* 146: 249–259. doi:10.1016/j.matdes.2018.03.015.
- [42] Garcia-Gonzalez, D, Jayamohan, J, Sotiropoulos, SN, Yoon, SH, Cook, J, Siviour, CR, Arias A, Jérusalem, A, 2017. On the mechanical behaviour of PEEK and HA cranial implants under impact loading. *J. Mech. Behav. Biomed. Mater.* 69: 342–354. doi:10.1016/j.jmbbm.2017.01.012
- [43] Liu, B, Robertson, GP, Kim, DS, Guiver, MD, Hu, W, Jiang, Z, 2007. Aromatic poly(ether ketone)s with pendant sulfonic acid phenyl groups prepared by a mild sulfonation method for proton exchange membranes. *Macromol.* 40: 1934–1944. doi:10.1021/ma061705+.
- [44] Collins, AM, 2012. Chapter 5 – Physical Techniques. Elsevier, Amsterdam. doi:10.1016/B978-0-08-097172-8.00005-9.
- [45] Rimington, RP, Capel, AJ, Christie, SDR, Lewis, MP, 2017. Biocompatible 3D printed polymers: Via fused deposition modelling direct C2C12 cellular phenotype in vitro. *Biocompatible, Lab Chip.* 17: 2982–2993. doi:10.1039/c7lc00577f.
- [46] Rimington, RP, Capel, Player, DJ, Bibb, RJ, Christie, SDR, Lewis MP, 2018. Feasibility and biocompatibility of 3D-printed photopolymerized and laser sintered polymers for neuronal, myogenic, and hepatic cell types. *Macromol. Biosci.* 18: 1–12 doi:https://doi.org/10.1002/mabi.201800113.
- [47] Friend, J, Yeo, L, 2010. Fabrication of microfluidic devices using polydimethylsiloxane, *Biomicrofluidics.* 4.... doi:10.1063/1.3259624.
- [48] Corfield, GC, Wheatley, GW, Parker, DG, 1990. Synthesis and properties of polyetheretherketone–polydimethylsiloxane block copolymers. *J. Polym. Sci. Part A Polym.*

- Chem. 28: 2821–2836. doi:10.1002/pola.1990.080281019.
- [49] Ceseracciu, L, Heredia-Guerrero, JA, Dante, S, Athanassiou, A, Bayer, IS, 2015. Robust and biodegradable elastomers based on corn starch and polydimethylsiloxane (PDMS). *ACS Appl. Mater. Interfaces*. 7: 3742–3753. doi:10.1021/am508515z.
- [50] Mondal, S, Phukan, A, Ghatak, A, 2015. Estimation of solid–liquid interfacial tension using curved surface of a soft solid. *Proc. Natl. Acad. Sci.* 112: 12563–12568. doi:10.1073/pnas.1502642112.
- [51] Comyn, J, Mascia, L, Xiao, G, Parker, BM, 1996. Corona-discharge treatment of polyetheretherketone (PEEK) for adhesive bonding, *Int. J. Adhes. Adhes.* 16: 301–304. doi:10.1016/S0143-7496(96)00010-3.
- [52] Iqbal, HMS, Bhowmik, S, Benedictus, R, 2010. Surface modification of high performance polymers by atmospheric pressure plasma and failure mechanism of adhesive bonded joints. *Int. J. Adhes. Adhes.* 30: 418–424. doi:10.1016/j.ijadhadh.2010.02.007.
- [53] Sastri, VR, 2010. Chapter 4 - Material Requirements for Plastics used in Medical Devices, *Plastics in Medical Devices: Properties, Requirements and Applications*. William Andrew. doi:10.1016/B978-0-8155-2027-6.10004-2.
- [54] Anderson, NG, 2012. Chapter 5 - Solvent Selection, *Practical Process Research and Development*. Elsevier, Amsterdam. doi:10.1016/B978-0-12-386537-3.00005-8.
- [55] Lyu, S, Untereker, D, 2009. Degradability of polymers for implantable biomedical devices. *Int. J. Mol. Sci.* 10: 4033–4065. doi:10.3390/ijms10094033.
- [56] Camino, C, Lomakin, SM, Lazzari, M, 2001. Polydimethylsiloxane thermal degradation part 1. Kinetic aspects, *Polymer*. 42: 2395–2402. doi:10.1016/S0032-3861(00)00652-2.
- [57] González-Rivera, J, Iglío R, Barillaro G, Duce, C, Tinè, 2018. Structural and thermoanalytical characterization of 3D porous PDMS foam materials: The effect of impurities derived from a sugar templating process. *Polymers*. 10: 616. doi:10.3390/polym10060616.
- [58] Norkhairunnisa, M, Azizan, A, Mariatti M, Ismail H, Sim LC, 2012. Thermal stability and electrical behavior of polydimethylsiloxane nanocomposites with carbon nanotubes and carbon black fillers. *J. Compos. Mater.* 46: 903–910 doi:10.1177/0021998311412985.
- [59] Rivière, L, Caussé N, Lonjon, A, Dantras, É, Lacabanne, C (2016). Specific heat capacity and thermal conductivity of PEEK/Ag nanoparticles composites determined by Modulated-Temperature Differential Scanning Calorimetry. *Polym. Degrad. Stab.* 127: 98–104. doi:10.1016/j.polymdegradstab.2015.11.015.
- [60] Patel, P, Hull, TR, McCabe, RW, Flath, D, Grasmeder, J, Percy, M, 2010. Mechanism of thermal decomposition of poly(ether ether ketone) (PEEK) from a review of decomposition studies. *Polym. Degrad. Stab.* 95: 709–718. doi:10.1016/j.polymdegradstab.2010.01.024.
- [61] Lewicki, JP, Liggat, JJ, Patel, M, 2009. The thermal degradation behaviour of polydimethylsiloxane/montmorillonite nanocomposites. *Polym. Degrad. Stab.* 94: 1548–1557. doi:10.1016/j.polymdegradstab.2009.04.030.
- [62] Camino, G, Lomakin, SM, Lageard M, 2002. Thermal polydimethylsiloxane degradation. Part 2. The degradation mechanisms. *Polymer*. 43: 2011–2015. doi:10.1016/S0032-3861(01)00785-6.
- [63] Sun, JT, Huang, YD, Cao, HL, Gong GF, 2004. Effects of ambient-temperature curing agents on the thermal stability of poly(methylphenylsiloxane). *Polym. Degrad. Stab.* 85: 725–731. doi:10.1016/j.polymdegradstab.2004.03.018.
- [64] Hay, JN, Kemmish, DJ, 1987. Thermal decomposition of poly(aryl ether ketones). *Polymer*.

28: 2047-2051. doi:10.1016/0032-3861(87)90039-5.

[65] Day, M, Cooney, JD, Wiles, DM, 1990. The thermal degradation of poly(aryl-ether-ether-ketone) (PEEK) as monitored by pyrolysis-GC/MS and TG/MS. *J. Anal. Appl. Pyrolysis*. 18: 163-173. doi:10.1016/0165-2370(90)80005-9.

[66] Fragiadakis, D, Pissis, P, Bokobza, L, 2005. Glass transition and molecular dynamics in poly(dimethylsiloxane)/silica nanocomposites. *Polymer*. 46: 6001-6008. doi:10.1016/j.polymer.2005.05.080.

[67] Diez-Pascual, AM, Martínez, G, Gómez, MA, 2009. Synthesis and characterization of poly(ether ether ketone) derivatives obtained by carbonyl reduction. *Macromolecules*. 42: 6885–6892. doi:10.1021/ma901208e.

[68] Garcia-Gonzalez, D, Rusinek, A, Jankowiak, T, \Arias A, 2015. Mechanical impact behavior of polyether-ether-ketone (PEEK). *Compos. Struct*. 124: 88-99. doi:10.1016/j.compstruct.2014.12.061.

[69] Aranguren, MI, 1998. Crystallization of polydimethylsiloxane: Effect of silica filler and curing. *Polymer*. 39: 4837-4903. doi:10.1016/S0032-3861(97)10252-X.

[70] Klonos, PA, 2018. Crystallization, glass transition, and molecular dynamics in PDMS of low molecular weights: A calorimetric and dielectric study. *Polymer* 159: 169–180. doi:doi.org/10.1016/j.polymer.2018.11.028.

[71] Kim, TK, Kim, JK, Jeong, OC, 2011. Measurement of nonlinear mechanical properties of PDMS elastomer. *Microelectron. Eng*. 88: 1982–1985. doi:10.1016/j.mee.2010.12.108.

[72] Liu, M, Chen, Q, 2009. Influences of heating temperature on mechanical properties of polydimethylsiloxane. *Sensors Actuators, A Phys*. 151: 42–45. doi:10.1016/j.sna.2009.02.016.doi:10.1016/j.sna.2009.02.016.

[73] Schneider, F, Fellner, T, Wilde, J, Wallrabe, U, 2008. Mechanical properties of silicones for MEMS. 18: 1-9. doi:10.1088/0960-1317/18/6/065008.

[74] Johnston, ID, McCluskey, DK, Tan, CKL, Tracey, MC, 2014. Mechanical characterization of bulk Sylgard 184 for microfluidics and microengineering. *J. Micromech. Microeng*. 24.... doi:10.1088/0960-1317/24/3/035017.

[75] Meng, Q, Hu, J, 2009. A review of shape memory polymer composites and blends. *Compos. Part A Appl. Sci. Manuf*. 40: 1661-1672. doi:10.1016/j.compositesa.2009.08.011.

[76] Bareiro Ferreira, OJ, Bendo Demétrio, K, Loureiro dos Santos, LA, 2017. Nanostructured hydroxyapatite/polydimethylsiloxane composites obtained by reactive synthesis. *Compos. Part B Eng*. 121: 152-161. doi:10.1016/j.compositesb.2017.05.009.

[77] Sun, D, Li, BB, Xu, ZL, 2013. Preparation and characterization of poly(dimethylsiloxane)-polytetrafluoroethylene (PDMS-PTFE) composite membrane for pervaporation of chloroform from aqueous solution. *Korean J. Chem. Eng*. 30: 2059-2067. doi:10.1007/s11814-013-0147-z.

[78] Wang, X, Mu, B, Wang, H, 2015. Preparation and properties of thermoplastic polyurethane/ultra high molecular weight polyethylene blends. *Polym. Compos*. 36: 897-906. doi:10.1002/pc.23009.

[79] Selvam, S, Marimuthu, K, 2016. Development and investigation of mechanical properties of PEEK fine particles reinforced UHMWPE composites. 11: 1298-1303. *Int. J. Appl. Eng. Res*.

[80] Bijwe, J, Sen, S, Ghosh, A, 2005. Influence of PTFE content in PEEK-PTFE blends on mechanical properties and tribo-performance in various wear modes. *Wear*. 258: 1536-1542.

doi:10.1016/j.wear.2004.10.008.

- [81] Abu Bakar MS, Chenag P, Khor KA, 2003. Mechanical properties of injection molded hydroxyapatite-polyetheretherketone biocomposites. *Compos. Sci. Technol.* 63: 421-425. doi:10.1016/S0266-3538(02)00230-0.
- [82] Hanson, DE, Hawley, M, Houlton, R, Chitanvis, K, Rae, P, Orlor, EB, Wroblewski, DA, 2005. Stress softening experiments in silica-filled polydimethylsiloxane provide insight into a mechanism for the Mullins effect. *Polymer*. 46: 10989–10995. doi:10.1016/j.polymer.2005.09.039.
- [83] Caruso, MM, Davis, DA, Shen, Q, Odom, SA, Sottos, NR, White, SR, Moore, JS, 2009. Mechanically-induced chemical changes in polymeric materials. *Chem. Rev.* 109: 5755-5798. doi:10.1021/cr9001353.
- [84] Schümann, K, Röhr, U, Schmitz, KP, Grabow, N, 2016. Conversion of engineering stresses to Cauchy stresses in tensile and compression tests of thermoplastic polymers. *Curr. Dir. Biomed. Eng.* 2: 649-652. doi:10.1515/cdbme-2016-0142.
- [85] Eirich, FR, 1973. Failure modes of elastomers. *Eng. Fract. Mech.* 5: 555-562. doi:10.1016/0013-7944(73)90040-4.
- [86] Richeton, J, Ahzi, S, Vecchio, KSS, Jiang, FCC, Adharapurapu, RRR, 2006. Influence of temperature and strain rate on the mechanical behavior of three amorphous polymers: Characterization and modeling of the compressive yield stress. *Int. J. Solids Struct.* 43: 2318-2335. doi:10.1016/j.ijsolstr.2005.06.040.
- [87] Li, J, Liu, H, Wang, C, Huang, G, 2017. A facile method to fabricate hybrid hydrogels with mechanical toughness using a novel multifunctional cross-linker. *RSC Adv.* 7: 35311–35319. doi:10.1039/c7ra05645a.
- [88] Gagliardi, S, Arrighi, V, Ferguson, R, Telling, MTF, 2001. Restricted dynamics in polymer-filler systems. *Phys. B Condens. Matter.* 301: 110-114. doi:10.1016/S0921-4526(01)00520-8.
- [89] Ansorge, S, Papailiou, K, 2015. Mechanical properties of silicone rubber under high loadings of alumina trihydrate filler. *J. Elastomers Plast.* 48: 354–382. doi:10.1177/0095244315580452.
- [90] Bokobza, L, 2017. Mechanical and electrical properties of elastomer nanocomposites based on different carbon nanomaterials. *C. 3: 10.* doi:10.3390/c3020010.
- [91] Tran, TN, Bayer, LS, Heredia-Guerrero, JA, Frugone, M, Lagomarsino, M, Maggio, F, Athanassiou, A, 2017. Cocoa shell waste biofilaments for 3D printing applications. *Macromol. Mater. Eng.* 302: 1-10. doi:10.1002/mame.201700219.
- [92] Aziz, T, Waters, M, Jagger, R, 2003. Analysis of the properties of silicone rubber maxillofacial prosthetic materials. *J. Dent.* 31: 67–74. doi:10.1016/S0300-5712(02)00084-2.
- [93] Griffin, MF, Leung, BC, Premakumar, Y, Szarko, M, Butler, PE, 2017. Comparison of the mechanical properties of different skin sites for auricular and nasal reconstruction. *J. Otolaryngol. - Head Neck Surg.* 46.... doi:10.1186/s40463-017-0210-6.
- [94] Pawlaczyk, M, Lelonkiewicz, M, Wiczerowski, M, 2013. Age-dependent biomechanical properties of the skin. *Postep. Dermatologii i Alergol.* 30: 302–306. doi:10.5114/pdia.2013.38359.
- [95] Traini, T, Mangano, C, Sammons, RL, Mangano, F, Macchi, A, Piattelli, A, 2008. Direct laser metal sintering as a new approach to fabrication of an isoelastic functionally graded material for manufacture of porous titanium dental implants. *Dent. Mater.* 24: 1225-1233. doi:10.1016/j.dental.2008.03.029. doi:10.1016/j.dental.2008.03.029.

- [96] Petit, C, Montanaro, L, Palmero, P, 2018. Functionally graded ceramics for biomedical application: Concept, manufacturing, and properties. *Int. J. Appl. Ceram. Technol.* 15: 820-840. doi:10.1111/ijac.12878.
- [97] Norman, J, Madurawe, RD, Moore, CMV, Khan, MA, Khairuzzaman, A, 2017. A new chapter in pharmaceutical manufacturing: 3D-printed drug products. *Adv. Drug Deliv. Rev.* 108: 39-50. doi:10.1016/j.addr.2016.03.001.
- [98] Kokkinis, D, Bouville, F, Studart, AR, 2018. 3D printing of materials with tunable failure via bioinspired mechanical gradients. *Adv. Mater.* 30: 1705808. doi:10.1002/adma.201705808.
- [99] Kawai, T, Shanjani, Y, Fazeli, S, Goodman, SB, Yang, YP, 2017. Customized load-bearing and degradable functionally-graded scaffold for improved treatment of early stage osteonecrosis of the femoral head. *J. Orthop. Res. Conf.* 36: 002-1011. doi: 10.1002/jor.23673.
- [100] Lima, DD, Mantri, SA, Mikler, CV, Contieri, R, Yannetta, CJ, Campo, KN, Lopes, ES, Styles, MJ, Borkar, T, Caram, R, Banerjee, R, 2017. Laser additive processing of a functionally graded internal fracture fixation plate. *Mater. Des.* 130: 8-15. doi:10.1016/j.matdes.2017.05.034.
- [101] Bos, EJ, Pluemeekers, M, Helder, M, Kuzmin, N, van der Laan, K, Groot, ML, van Osch, G, van Zuijlen, P, 2018. Structural and mechanical comparison of the human ear, alar, and septal cartilage, *Plast. Reconstr. Surg. Glob. Open.* 6:.... Doi:10.1097/GOX.0000000000001610.
- [102] Rieske, P, Krynska, B, Azizi, SA, 2005. Human fibroblast-derived cell lines have characteristics of embryonic stem cells and cells of neuro-ectodermal origin. *Differentiation*, 73: 474-483. doi:10.1111/j.1432-0436.2005.00050.x.
- [103] Morrison, C, Macnair, R, Macdonald, C, Wykman, A, Goldie, L, Grant, MH, 1995. In-vitro biocompatibility testing of polymers for orthopedic implants using cultured fibroblasts and osteoblasts. *Biomater.* 16: 987-992. doi:10.1016/0142-9612(95)94906-2.
- [104] Tamada, Y, Ikada, Y, 1994. Fibroblast growth on polymer surfaces and biosynthesis of collagen, *J. Biomed. Mater. Res.* 28: 783-789. doi:10.1002/jbm.820280705.
- [105] do Nascimento, MHM, Ferreira, M, Malmonge, SM, Lombello, 2017. CB, Evaluation of cell interaction with polymeric biomaterials based on hyaluronic acid and chitosan. *J. Mater. Sci. Mater. Med.* 28: 68. doi:10.1007/s10856-017-5875-x.
- [106] Bačáková, L, Filová, E, Rypáček, F, Švorčík, V, Starý, V, 2004. Cell adhesion on artificial materials for tissue engineering. *Physiol. Res.* 53: 35-45. doi:10.1088/0957-4484/21/48/485703.
- [107] Gauvin, R, Guillemette, M, Galbraith, T, Bourget, JM, Larouche, D, Marcoux, H, Aubé, D, Hayward, C, Auger, FA, Germain, L, 2011. Mechanical properties of tissue-engineered vascular constructs produced using arterial or venous cells. *Tissue Eng. Part A.* 17: 15-16. doi:10.1089/ten.tea.2010.0613.