

---

This item was submitted to [Loughborough's Research Repository](#) by the author.  
Items in Figshare are protected by copyright, with all rights reserved, unless otherwise indicated.

## **Supplementary Information Figures for Effect of Mass Transport on the Electrochemical Oxidation of Alcohols over Electrodeposited film and Carbon- Supported Pt electrodes**

PLEASE CITE THE PUBLISHED VERSION

LICENCE

CC BY 4.0

REPOSITORY RECORD

Lin, Wen-Feng, Vinod Kumar Puthiyapura, Andrea E. Russell, Dan J. L. Brett, and Christopher Hardacre. 2018. "Supplementary Information Figures for Effect of Mass Transport on the Electrochemical Oxidation of Alcohols over Electrodeposited Film and Carbon- Supported Pt Electrodes". figshare. <https://doi.org/10.17028/rd.lboro.5993131.v1>.

## Supplementary Information

# Effect of Mass Transport on the Electrochemical Oxidation of Alcohols over Electrodeposited film and Carbon- Supported Pt electrodes

Vinod Kumar Puthiyapura<sup>1</sup>, Wen-Feng Lin<sup>\*,2</sup>, Andrea E Russell<sup>3</sup>, Dan J L Brett<sup>4</sup>, Christopher Hardacre<sup>\*,1</sup>

<sup>1</sup>School of Chemical Engineering and Analytical Science, The University of Manchester, Manchester- M13 9PL, UK.

<sup>2</sup>Department of Chemical Engineering, Loughborough University, Loughborough, Leicestershire- LE1 13TU, UK

<sup>3</sup>Department of Chemistry, University of Southampton, High field, Southampton- SO17 1BJ, UK

<sup>4</sup>Department of Chemical Engineering, University College London (UCL), London- WC1E 7JE, UK.




Figure S1. A typical voltammogram of electrodeposited Pt in 0.1M HClO<sub>4</sub> solution. Scan rate 50 mVs<sup>-1</sup>. Pt active area ( $A_r$ ) was calculated from the  $H_{UPD}$  desorption region.




Figure S2. The effect of electrode rotation on peak  $a_2$  current for electrodeposited Pt film in solutions of (a) 0.5M methanol+0.1M HClO<sub>4</sub> (b) 0.5M ethanol+0.1M HClO<sub>4</sub> (c) 0.5M *n*-butanol+0.1M HClO<sub>4</sub> (d) 0.1M 2-butanol+0.1M HClO<sub>4</sub>. Scan rate 50 mVs<sup>-1</sup>.




Figure S3. The effect of electrode rotation rate on peak  $a_1$  current density of electrodeposited Pt film on 0.1 M 2-butanol+0.1 M HClO<sub>4</sub> where electrode rotation changed from 0 rpm to 900 rpm directly. The rotation rate changed from A to B (increase & then decrease in  $\omega$ ) and C to D (increase in  $\omega$ ) as given in the figure.




Figure S4. The effect of electrode rotation rate on peak  $a_2$  current density for Pt/C(40%) catalyst in 0.5M alcohol + 0.1M  $\text{HClO}_4$  solution of (a) methanol (b) ethanol (c) *n*-butanol (d) 2-butanol. Scan rate  $50 \text{ mVs}^{-1}$ .




Figure S5. Koutecky-Levich plot of ethanol oxidation reaction on Pt/C at 0.75 V.