


This item was submitted to Loughborough's Institutional Repository (<https://dspace.lboro.ac.uk/>) by the author and is made available under the following Creative Commons Licence conditions.



CC creative commons
COMMONS DEED

Attribution-NonCommercial-NoDerivs 2.5

You are free:

- to copy, distribute, display, and perform the work

Under the following conditions:

BY: **Attribution.** You must attribute the work in the manner specified by the author or licensor.

Noncommercial. You may not use this work for commercial purposes.

No Derivative Works. You may not alter, transform, or build upon this work.

- For any reuse or distribution, you must make clear to others the license terms of this work.
- Any of these conditions can be waived if you get permission from the copyright holder.

Your fair use and other rights are in no way affected by the above.

This is a human-readable summary of the [Legal Code \(the full license\)](#).

[Disclaimer](#) 

For the full text of this licence, please go to:
<http://creativecommons.org/licenses/by-nc-nd/2.5/>

Production of silica particles by membrane emulsification

Marijana M. Dragosavac¹, Richard G Holdich¹, Goran T. Vladislavljević¹, Miguel Angel Suarez Valdes² and Michael T. Stillwell³

¹Chemical Engineering, Loughborough University, Loughborough, UK

²Chemical Engineering and Environmental Technology, University of Oviedo, Oviedo, Spain

³Micropore Technologies, Hatton, Derby, DE65 5DU

Keywords: membrane emulsification, silica particles, Dispersion cell, emulsion

In the last few years there has been increasing interest in the production of porous inorganic materials with high surface area. Such materials have potential application in various fields of catalysis, separation, sorption, bioreactor, sensors and so on. Silica is an inorganic material that does not swell and with its good mechanical and thermal stability it can be used in various solvents and have wide applications. In the literature silicon alkoxide or tetraetoxisilane are mainly used as silica sources. The main drawback of using such materials is that they are expensive and therefore production of large quantities of silica would not be cost effective.

In this work silica particles were successfully produced from precursor sodium silicate droplets using membrane emulsification. In membrane emulsification monosized emulsion is produced by injecting one liquid phase (e.g. water) through microporous membrane into a second immiscible liquid phase (e.g. kerosene). The droplet size is mainly controlled by the shear stress applied on the membrane surface and the pore size (Vladislavljević and Williams 2005).

The Dispersion Cell (Kosvintsev et. al 2005) with a hydrophobic nickel membrane attached on the bottom of the cell (Fig. 1 a,b) was used to generate emulsion. A mixture of sodium silicate (silica source) and sulphuric acid (gel-forming reagent) was used as dispersed phase and kerosene containing 2% Span 80 was used as a continuous phase.




Figure 1. (a) Hydrophobic nickel membrane with 15 μm pores and (b) Dispersion Cell both kindly provided by Micropore Ltd. UK. (c) SEM of calcined silica particles with a mean size of

In most of the experiments flux of the dispersed phase was kept constant at 350 L m⁻² h⁻¹. It is widely accepted that the shear stress on the membrane surface has to be applied in order to get uniform droplets. In the Dispersion cell the shear stress is induced with the paddle stirrer placed on top of the membrane. By changing the shear stress on the membrane surface liquid silica droplets in the range between 50 and 160 μm were produced. After solidification of silica particles were washed and dried at room temperature followed by calcination at 550°C. After final drying the size of the produced silica particles was in the range between 30 and 70 μm (Fig. 1c). BET specific surface area of the produced silica after calcination was found to be 750 m²/g while the average pore diameter was 1.3 nm.

Acknowledgment

The authors wish to acknowledge the financial support of the UK Engineering and Physical Sciences Research Council. The work was undertaken as part of the DIAMOND project into Decommissioning, Immobilisation And Management Of Nuclear wastes for Disposal.

References

Kosvintsev S.R, Gasparini G., Holdich R.G., Cumming I.W, Stillwell M.T., Liquid-Liquid membrane Dispersion in a Stirred Cell with and without Controlled Shear, *Industrial and Engineering Chemistry Research* , 44, 2005, 9323.

Vladisavljević, G.T. and Williams, R.A., Recent developments in manufacturing emulsions and particulate products using membranes, *Advances in Colloid and Interface Science*, 113, 2005, 1.